



FOAMULAR® & FOAMULAR® NGX® THERMAPINK® 25

EXTRUDED POLYSTYRENE (XPS) RIGID FOAM INSULATION

Owens Corning® FOAMULAR® & FOAMULAR® NGX® THERMAPINK® 25 Extruded Polystyrene (XPS) insulations are closed-cell, moisture-resistant rigid foam boards specially designed for roofing applications. FOAMULAR® & FOAMULAR® NGX® THERMAPINK® 25 can also be used in tapered insulation systems. See “FOAMULAR® Tapered Insulation System Technical Guide” for more information.

FOAMULAR® NGX® THERMAPINK® 25 contains the additional benefit of being manufactured with a blowing agent formulation that delivers a 90% reduction to Global Warming Potential (100 years), including the complete elimination of HFC 134a.¹

1 Compared to FOAMULAR® THERMAPINK® 25 blowing agent formulation.


Features



**SUPERIOR
MOISTURE
RESISTANCE**



DURABLE



**EASY TO CUT,
FORM & FIT**

Standards, Codes Compliance

- Meets ASTM C578 Type IV (THERMAPINK® 25 insulation)
- UL (Underwriters Laboratories) Roof Deck Constructions, tested in accordance with UL 1256, “Standard for Fire Test of Roof Deck Constructions”
- UL Classified; a copy of UL Classification Certificate U-197 is available at www.owenscorning.com
- See UL ER8811-01 at UL.com
- Factory Mutual (FM) Class 1 Roof Decks
- ASTM E108 Fire Classified Assemblies
- ASTM E119 Fire Resistance Rated Roof/Ceiling Assemblies
- UL and FM Wind Uplift Rated Assemblies
- Meets California Quality Standards and HUD UM #71a

Physical Properties²

PROPERTY	TEST METHOD ³	VALUE
Thermal Resistance, ⁴ R-Value, hr·ft ² ·°F/Btu (RSI, °C·m ² /W) @ 75°F (24°C) mean temperature	ASTM C518	5.0 (0.88)
@ 40°F (4.4°C) mean temperature		5.4 (0.95)
@ 25°F (-3.9°C) mean temperature		5.6 (0.99)
Long-Term Thermal Resistance, LTTR-Value, ⁴ minimum hr·ft ² ·°F/Btu (RSI, °C·m ² /W) @ 75°F (24°C) mean temperature	CAN/ULC S770-03	5.0 (0.88)
Compressive Strength, ⁵ minimum psi (kPa)	ASTM D1621	25 (172)
Flexural Strength, ⁶ minimum psi (kPa)	ASTM C203	50 (345)
Water Absorption, ⁷ maximum % by volume	ASTM C272	0.3
Water Vapor Permeance, ⁸ maximum perm (ng/Pa·s·m ²)	ASTM E96	1.5 (86)
Dimensional Stability, maximum % linear change	ASTM D2126	2.0
Flame Spread ^{9,10}	ASTM E84	10
Smoke Developed ^{9,10}	ASTM E84	175
Oxygen Index, ⁹ minimum % by volume	ASTM D2863	24
Service Temperature, maximum °F (°C)	-	165 (74)
Linear Coefficient of Thermal Expansion, in/in/°F (m/m/°C)	ASTM E228	3.5 x 10 ⁻⁵ (6.3 x 10 ⁻⁵)

- Properties shown are representative values for 1-inch-thick material, unless otherwise specified. Extruded Polystyrene Insulation may exhibit different physical properties based upon thickness. Certain physical properties are listed by minimum and maximum values per ASTM C578. For details on specific test methods, please contact Owens Corning at 1-800-GET-PINK.
- Modified as required to meet ASTM C578.
- R means the resistance to heat flow; the higher the value, the greater the insulation power. This insulation must be installed properly to get the marked R-value. Follow the manufacturer's instructions carefully. If a manufacturer's fact sheet is not provided with the material shipment, request this and review it carefully. R-values vary, depending on many factors, including the mean temperature at which the test is conducted and the age of the sample at the time of testing. Because rigid foam plastic insulation products are not all aged in accordance with the same standards, it is useful to publish comparison R-value data. The R-value for FOAMULAR® & FOAMULAR® NGX® XPS insulation is provided from testing at mean temperatures of: -4°C (25°F), 4.4°C (40°F), and 24°C (75°F), and aging techniques of 180-day real-time aged (as mandated by ASTM C578) and accelerated aging “Long-Term Thermal Resistance” (LTTR) per CAN/ULC S770-03. The R-value at 180-day real-time age and 75°F mean temperature is commonly used to compare products and is the value printed on the product.
- Value at yield or 10% deflection, whichever occurs first.
- Value at yield or 5%, whichever occurs first.
- Data ranges from 0.00 to value shown due to the level of precision of the test method.
- Water vapor permeance decreases as thickness increases.
- These laboratory tests are not intended to describe the hazards presented by this material under actual fire conditions.
- Data from Underwriters Laboratories Inc.® classified. See Classification Certificate U-197.

Technical Information

- FOAMULAR® & FOAMULAR® NGX® XPS insulations are non-structural materials and must be installed on framing that is independently braced and structurally adequate to meet required construction and service-loading conditions.
- FOAMULAR® & FOAMULAR® NGX® XPS insulations can be exposed to the exterior during normal construction cycles. During that time, some fading of color may begin due to UV exposure, and, if exposed for extended periods of time, some degradation or “dusting” of the polystyrene surface may begin. It is best if the product is covered within 60 days to minimize degradation. Once covered, the deterioration stops, and damage is limited to the thin top surface layers of cells. Cells below are generally unharmed and still useful insulation.
- FOAMULAR® & FOAMULAR® NGX® XPS insulations have a maximum service temperature of 165°F. Taking simple precautions during construction can minimize the potential for heat-related damage. Install only as much FOAMULAR® & FOAMULAR® NGX® XPS insulation as can be covered in the same day. For horizontal applications, always turn the print side down so the black print does not show to the sun, which may at times act as a solar collector, raising the temperature of the foam under the print to an unacceptable level. Provide a final finish covering or temporary white opaque covering to avoid possible damage when dark (non-white) surfaces are used over FOAMULAR® & FOAMULAR® NGX® insulation. Do not cover FOAMULAR® or FOAMULAR® NGX® XPS insulation, either stored (factory-wrapped or unwrapped) or partially installed, with dark-colored (non-white) or clear (non-opaque) coverings and leave it exposed to the sun. If improperly covered and exposed to the right combination of sun, time, and temperature, FOAMULAR® & FOAMULAR® NGX® insulation deformation damage may occur rapidly. See [“FOAMULAR® Extruded Polystyrene \(XPS\) Insulation Heat Buildup Due to Solar Exposure Technical Bulletin”](#) for more information.
- This product is combustible. A protective barrier or thermal barrier is required as specified in the appropriate building code.
- All construction should be evaluated for the necessity to provide vapor retarders. See current “ASHRAE Handbook of Fundamentals.”

Certifications and Sustainable Features

- Certified by SCS Global Services to contain an average of 20% recycled content pre-consumer.
- GREENGUARD Certified products are certified to GREENGUARD standards for low chemical emissions into indoor air during product usage. For more information, visit ul.com/gg.
- Environmental Product Declaration (EPD) has been certified by UL Environment.
- Utilizing FOAMULAR® & FOAMULAR® NGX® XPS insulation can help builders achieve green building certifications, including the U.S. Green Building Council’s Leadership in Energy and Environmental Design (LEED®) certification.
- UL CERTIFIED — See Bulk Shipment Certificate U-197, available at www.owenscorning.com/U197.



Product and Packaging Data¹¹

MATERIAL			PACKAGING						EDGES
THICKNESS (IN)	PRODUCT DIMENSIONS THICKNESS X WIDTH X LENGTH (IN)	PALLET (UNIT) DIMENSIONS (TYPICAL) WIDTH X LENGTH X HEIGHT (FT)	SQUARE FT PER PALLET	BOARD FT PER PALLET	BUNDLES PER PALLET	PIECES PER BUNDLE	PIECES PER PALLET		
Extruded polystyrene closed-cell foam, ASTM C578 Type IV, 25 psi minimum			Shipped in poly-wrapped units with individually wrapped or banded bundles						
1	1 x 48 x 96	4 x 8 x 8	3,072	3,072	8	12	96	Square	
1½	1.5 x 48 x 96	4 x 8 x 8	2,048	3,072	8	8	64		
2	2 x 48 x 96	4 x 8 x 8	1,536	3,072	8	6	48		
3	3 x 48 x 96	4 x 8 x 8	1,024	3,072	8	4	32		
4	4 x 48 x 96	4 x 8 x 8	768	3,072	8	3	24		

11 Product availability and lead times vary by region and by product. Consult your local Owens Corning sales representative for availability and lead times.

Environmental and Sustainability

Owens Corning is a worldwide leader in building material systems, insulation, and composite solutions, delivering a broad range of high-quality products and services. Owens Corning is committed to driving sustainability by delivering solutions, transforming markets, and enhancing lives. More information can be found at www.owenscorning.com.

FOAMULAR® and FOAMULAR® NGX® XPS insulation use blowing agents with zero ozone depletion potential.

Detailed environmental information on the lifecycle of this product can be found in product’s Environmental Product Declaration:

- “FOAMULAR® XPS Insulation Environmental Product Declaration”
- “FOAMULAR® NGX® XPS Insulation Environmental Product Declaration”

Disclaimer of Liability

Technical information contained herein is furnished without charge or obligation and is given and accepted at recipient’s sole risk. Because conditions of use may vary and are beyond our control, Owens Corning makes no representation about, and is not responsible or liable for, the accuracy or reliability of data associated with particular uses of any product described herein. Nothing contained in this bulletin shall be considered a recommendation.

Notes

For additional information, refer to the Safe Use Instruction Sheet (SUIS) found in the SDS Database via <http://sds.owenscorning.com>.

Flute Span Capability^{12, 13, 14}

STEEL DECK TYPE ¹⁵	THERMAPINK® 25	RIB OPENING, WIDTH	RIB DEPTH
A (narrow rib)	1"	1"	1½"
F (intermediate rib)	1"	1¾"	1½"
B (wide rib)	1½"	2¾"	1½"
3DR (deep rib)	1½"	2¾"	3" and greater
Long Span	1½"	3¾"	3" and greater
	2"	4¾"	3" and greater
Cellular	Not Permitted ¹	Varies	Varies
Acoustical	Not Permitted ¹	Varies	Varies

12 See Underwriters Laboratories Roof Deck Construction #457 for full assembly details. Fire tested in accordance with ANSI/UL 1256, Fire Test of Roof Deck Constructions.

13 Data provided is derived from testing in general accordance with FM 4450 and FM 4470 resistance to foot traffic requirements.

14 FM Class 1 under-deck fire ratings are not achieved by XPS direct to steel deck assemblies.

15 Minimum steel deck depth permitted is 1½ inches. Minimum 22 MSG. Cellular and acoustical decks were not tested, and are therefore not permitted.

Limited Warranty

FOAMULAR® & FOAMULAR® NGX® XPS insulation limited lifetime warranty maintains 90% of its R-value for the lifetime of the building and covers all ASTM C578 properties. See [“FOAMULAR® Extruded Polystyrene Insulation Lifetime Limited Warranty”](#) for complete details, limitations, and requirements.

OWENS CORNING FOAM INSULATION, LLC
ONE OWENS CORNING PARKWAY
TOLEDO, OH 43659 USA

1-800-GET-PINK®
www.owenscorning.com

Pub. No. 23546-O. Printed in U.S.A. October 2023.
The color PINK is a registered trademark of Owens Corning.
© 2023 Owens Corning. All Rights Reserved.