



FOAMULAR® INSULPINK®

Extruded Polystyrene (XPS) Rigid Foam Insulation

Product Data Sheet



Energy-Saving, Moisture-Resistant XPS Insulation

Recessed Furring-Ready Insulation

ASTM C578 Type X, 15 psi minimum

Description

INSULPINK® extruded polystyrene (XPS) insulation is extremely light-weight for easy handling and provides a high R-value of 7.5, exceptional resistance to moisture, and pre-cut slotted edges ready to accommodate 1x3 wood furring for easy installation.

INSULPINK® insulation is produced by Owens Corning's patented Hydrovac® process technology under conditions of strict quality control. Used to insulate the interior of basement or other concrete or block walls, INSULPINK® insulation accommodates a nailing strip which is used to attach the foam boards to the wall and provide framing to attach the finish surface such as drywall.

Key Features

- Helps reduce job site labor costs while you install premium insulation
- Available in a thickness of 1½" with slotted edges to accommodate furring
- Excellent long-term stable insulating performance with an R-value of R-7.5¹
- Exceptional moisture resistance, long-term durability
- Limited lifetime warranty²— maintains 90% of R-value and covers all ASTM C578 properties
- GREENGUARD Gold Certified
- The only XPS foam with certified recycled content— certified by SCS Global Services to contain a minimum 20% recycled content
- Will not corrode, rot or support mold growth
- Zero ozone depletion potential with 70% less global warming potential than our previous formula
- Reusable
- Lightweight, durable rigid foam panels are easy to handle and install
- Easy to saw, cut or score

Technical Information

This product is combustible and when used on interior surfaces, it cannot be left exposed. A protective barrier or thermal barrier is required as specified in the appropriate building code. For additional information, consult MSDS or contact Owens Corning World Headquarters at 1-800-GET-PINK®.

All construction should be evaluated for the necessity to provide vapor retarders. See current ASHRAE Handbook of Fundamentals.

FOAMULAR® INSULPINK® insulation is a non-structural material.

FOAMULAR® insulation can be exposed to the exterior during normal construction cycles. During that time some fading of color may begin due to UV exposure, and, if exposed for extended periods of time, some degradation or "dusting" of the polystyrene surface may begin. It is best if the product is covered within 60 days to minimize degradation. Once covered, the deterioration stops, and damage is limited to the thin top surface layers of cells. Cells below are generally unharmed and still useful insulation.



FOAMULAR® INSULPINK®

Extruded Polystyrene (XPS) Rigid Foam Insulation

Product Data Sheet

Standards, Codes Compliance

- Meets ASTM C578 Type X
- UL Classified. A copy of UL Classification Certificate U-197 is available at www.foamular.com
- See UL ER8811-01 at UL.com
- ASTM E119 Fire Resistance Rated Wall Assemblies. See www.foamular.com for details.
- Meets California Quality Standards and HUD UM #71A
- Compliance verification by RADCO (AA-650)



Certifications and Sustainable Features of FOAMULAR® XPS insulation

- FOAMULAR® XPS insulation is reusable
- FOAMULAR® XPS insulation is made with a zero ozone depletion formula
- Certified by SCS Global Services to contain a minimum of 20% recycled content
- Certified to meet indoor air quality standards under the stringent GREENGUARD Indoor Air Quality Certification Program, and the GREENGUARD Gold Certification.

Typical Physical Properties¹

FOAMULAR® INSULPINK® XPS Insulation

Property	Test Method ²	Value
Thermal Resistance³ , R-Value (180 day) minimum, hr•ft ² •°F/Btu (RSI, °C•m ² /W) @ 75°F (24°C) mean temperature, 1.5" Thickness @ 40°F (4.4°C) mean temperature, 1.5" Thickness	ASTM C518	7.5 (1.32) 8.1 (1.43)
Long Term Thermal Resistance , LTTR-Value ³ , minimum hr•ft ² •°F/Btu (RSI, °C•m ² /W) @ 75°F (24°C) mean temperature, 1.5" Thickness	CAN/ULC S770-03	7.8 (1.37)
Compressive Strength⁴ , minimum psi (kPa)	ASTM D1621	15 (103)
Flexural Strength⁵ , minimum psi (kPa)	ASTM C203	60 (414)
Water Absorption⁶ , maximum % by volume	ASTM C272	0.10
Water Vapor Permeance⁷ , maximum perm (ng/Pa•s•m ²)	ASTM E96	1.5 (86)
Dimensional Stability , maximum % linear change	ASTM D2126	2.0
Flame Spread^{8,9}	ASTM E84	5
Smoke Developed^{8,9,10}	ASTM E84	45-175
Oxygen Index⁸ , minimum % by volume	ASTM D2863	24
Service Temperature , maximum °F (°C)	—	165 (74)
Linear Coefficient of Thermal Expansion , in/in/°F (m/m/°C)	ASTM E228	3.5 x 10 ⁻⁵ (6.3 x 10 ⁻⁵)

1. Properties shown are representative values for 1" thick material, unless otherwise specified.
2. Modified as required to meet ASTM C578.
3. R means the resistance to heat flow; the higher the value, the greater the insulation power. This insulation must be installed properly to get the marked R-value. Follow the manufacturer's instructions carefully. If a manufacturer's fact sheet is not provided with the material shipment, request this and review it carefully. R-values vary depending on many factors including the mean temperature at which the test is conducted, and the age of the sample at the time of testing. Because rigid foam plastic insulation products are not all aged in accordance with the same standards, it is useful to publish comparison R-value data. The R-value for FOAMULAR® XPS insulation is provided from testing at two mean temperatures, 40°F and 75°F, and from two aging (conditioning) techniques, 180 day real-time aged (as mandated by ASTM C578) and a method of accelerated aging sometimes called "Long Term Thermal Resistance" (LTTR) per CAN/ULC S770-03. The R-value at 180 day real-time age and 75°F mean temperature is commonly used to compare products and is the value printed on the product.
4. Values at yield or 10% deflection, whichever occurs first.
5. Value at yield or 5%, whichever occurs first.
6. Data ranges from 0.00 to value shown due to the level of precision of the test method.
7. Water vapor permeance decreases as thickness increases.
8. These laboratory tests are not intended to describe the hazards presented by this material under actual fire conditions.
9. Data from Underwriters Laboratories Inc.® classified. See Classification Certificate U-197.
10. ASTM E84 is thickness-dependent, therefore a range of values is given.

- Qualified as an ENERGY STAR® product, under the U.S. Environmental Protection Agency and the U.S. Department of Energy
- Approved under the Home Innovation Research Labs NGBS Green Certification Program
- Utilizing FOAMULAR® XPS insulation can help achieve green building certifications including the U.S. Green Building Council's Leadership in Energy and Environmental Design (LEED®) certification
- FOAMULAR® XPS insulation may qualify for The Buy American provision of the American Recovery and Reinvestment Act (ARRA)

Environmental and Sustainability

Owens Corning is a worldwide leader in building material systems, insulation and composite solutions, delivering a broad range of high-quality products and services. Owens Corning is committed to driving sustainability by delivering solutions, transforming markets and enhancing lives. More information can be found at www.sustainability.owenscorning.com.



FOAMULAR® INSULPINK® Extruded Polystyrene (XPS) Rigid Foam Insulation

Product Data Sheet

Product and Packaging Data

FOAMULAR® INSULPINK® XPS Insulation

Material			Packaging							
Extruded polystyrene closed-cell foam panel			Shipped in poly-wrapped units with individually wrapped or banded bundles.							
Thickness (in)	Product Dimensions Thickness (in) x Width (in) x Length (in)		Pallet (Unit) Dimensions (typical) Width (ft) x Length (ft) x Height (ft)		Square feet per Pallet	Board feet per Pallet	Bundles per Pallet	Pieces per Bundle	Pieces per Pallet	Edges
1½	1.5 x 24 x 96 (Half unit)		4 x 8 x 4		1,024	1,536	4	16	64	Slotted to accommodate furring strips

1. Product availability and lead times vary by region and by product. Consult your local Owens Corning sales representative for availability and lead times.

Warranty

FOAMULAR® XPS Insulation limited lifetime warranty maintains 90% of its R-value for the lifetime of the building and covers all ASTM C578 properties. See actual warranty for complete details, limitations and requirements at www.foamular.com or www.owenscorningcommercial.com.

Notes

1. R means the resistance to heat flow; the higher the R-value, the greater the insulating power.
2. See actual warranty for complete details, limitations and requirements.

All products described here may not be available in all geographic markets. Consult your local sales office representative for more information.

For more information on the Owens Corning family of building products, contact your Owens Corning dealer, call 1-800-GET-PINK®, or access our web sites: www.foamular.com and www.owenscorning.com.



FOAMULAR® INSULPINK®

Extruded Polystyrene (XPS) Rigid Foam Insulation

Product Data Sheet

Disclaimer of Liability

Technical information contained herein is furnished without charge or obligation and is given and accepted at recipient's sole risk. Because conditions of use may vary and are beyond our control, Owens Corning makes no representation about, and is not responsible or liable for the accuracy or reliability of data associated with particular uses of any product described herein.

SCS Global Services provides independent verification of recycled content in building materials and verifies recycled content claims made by manufacturers. For more information, visit www.SCSglobalservices.com.

GREENGUARD Certified products are certified to GREENGUARD standards for low chemical emissions into indoor air during product usage. For more information, visit ul.com/gg.

This Home Innovation Research Labs Green Approved mark is your assurance that a product is eligible for points toward National Green Building Certification. Visit www.GreenApprovedProducts.com for details.

LEED is a registered trademark of the U.S. Green Building Council.



Home Innovation
NGBS GREEN CERTIFIED™



OWENS CORNING FOAM INSULATION, LLC
ONE OWENS CORNING PARKWAY
TOLEDO, OHIO 43659
1-800-GET-PINK®
www.owenscorning.com

Pub. No. 45203-D. Printed in U.S.A. February 2015. THE PINK PANTHER™ & ©1964-2015 Metro-Goldwyn-Mayer Studios Inc. All Rights Reserved. The color PINK is a registered trademark of Owens Corning. ©2015 Owens Corning. All Rights Reserved.

