



TRUMBULL #1126 SEBS MODIFIED ASPHALT

Uses

Trumbull's #1126 Modified Mopping Asphalt is suitable for use in Built-Up Roofing applications and Waterproofing treatment when specified.

Description

Trumbull # 1126 is formulated from selected petroleum based materials and blended with SEBS polymer to obtain a high softening point and mid-range penetration value. It is supplied hot in tank wagons or cold in cartons.

Typical Physical Properties

<u>Property</u>	<u>Range</u>
Color	Dark Brown to Black
Softening Point, ASTM D-36	195°F - 240°F
Penetration @ 77°F, ASTM D-5 100 grams, 5 sec.	25-40 dmm
Flash Point (COC), ASTM D-92	525 °F Minimum
Solubility in Trichloroethylene, ASTM D-2042	99.0% Minimum
Specific Gravity @ 60°F, ASTM D-70	1.000+/- 0.025
Weight / Gallon @ 60°F	8.32 +/- 0.2 lbs.
Elongation @ 77°F, ASTM D-412	>1000% (typical)
Equiviscous Temperature Range ASTM D-4402	TBD

Sept-01