



TRUMBULL BUILT-UP ROOFING ASPHALT

Description

Trumbull's Built-Up Roofing Asphalt products are manufactured from selected petroleum based materials and processed to various softening points and penetrations, meeting required specifications as outlined in ASTM D-312. It is supplied in tank vehicles and cartons.

Typical Physical Properties

<u>Property</u>	Type I	Type II	<u>Range</u> Type III	Type IV
Color	-----Dark Brown to Black-----			
Softening Point ASTM D-36	135-151°F	158-176°F	185-205°F	210-225°F
ASTM D-5 Penetration @ 77°F 100 grams, 5 sec.	18-60 dmm	18-40 dmm	15-35 dmm	12 - 25 dmm
ASTM D-5 Penetration @ 115°F 50 grams, 5 sec.	90-180 dmm	100 dmm max.	90 dmm max.	75 dmm max.
Flash Point (COC) ASTM D-92	----- 500°F minimum -----			
Solubility in trichloroethylene (%)	----- 99.0 minimum -----			

Sept-01