



TRUMBULL #6032 CUTBACK ASPHALT

Uses

Trumbull #6032 Cutback Asphalt is used as a base vehicle for the manufacture of various protective products and waterproofing compounds.

Description

Trumbull Cutback #6032 is formulated from selected steam and vacuum refined asphalts and cut with 100°F flash point Mineral Spirits to a semi-fluid consistency. It is supplied in a tank vehicles.

Typical Physical Properties

| <u>Property</u> | <u>Range</u> |
|---|---------------------|
| Color | Dark Brown to Black |
| Total Solids Content | 68 - 74% by weight |
| Solvent Content | 26 - 32% by weight |
| Solvent Type | Mineral Spirits |
| Flash Point (TCC), ASTM D-56 | 100 °F Minimum |
| Specific Gravity @ 60°F, ASTM D-1475 | 0.928 +/- 0.025 |
| Stomer Viscosity, ASTM D-562 | 120 - 150 seconds |
| Base Asphalt | |
| Softening Point, ASTM D-36 | 115°F - 130°F |
| Penetration @ 77°F, ASTM D-5 100 grams, 5 sec. | 60 - 110 dmm |

Sept-01