



973 & 973CX1 MULTI-END ROVING

Enhance surface aesthetics & performance

973 family of products represents a compelling solution for Sheet Molding Compound (SMC) Class A & semi-structural parts where efficient processing, superior surface finish and mechanical properties are required.

- ✔ 973 & 973CX1 multi-end rovings are made from Advantex® continuous glass filame
- ✔ These products are compatible with polyester and vinyl-ester resin systems; as well as polyurethane resins used in Long Fiber Injection (LFI) processes.

Product Benefits



Efficient Processability

- Proprietary sizing enables optimal processability in both SMC and LFI processes with: low static and fuzz, easy chopping without long fiber cuts, and excellent runnability with smooth unwinding.



High Mechanical Properties

- Optimal adherence to the resin matrix, along with excellent wetting characteristics provide enhanced mechanical properties in semi-structural applications.



Class A Surface Finish

- Excellent wetting characteristics allow lower sheet density, resulting in Class A surface quality in Low Profile SMC.



Enhanced Service Life

- Advantex® glass helps fight corrosion, enhancing service life compared to standard E-glass.

Application

973 & 973CX1 products are designed to provide optimal mechanical and aesthetics performance in Low Profile Class A automotive and semi- structural heavy truck applications. Good surface finish can also be achieved in LFI applications with in- mold coating.



Availability

Available worldwide — other Tex may be available upon request.

MANUFACTURING REGION	PRODUCT/DOFF DESCRIPTION	EXTERNAL Ø MM (IN)	HEIGHT MM (IN)	NET WEIGHT (KG/LB)
North America	973 4500 Tex	280; 305; 355 / 11; 12; 14	260 / 10.3	30/67.5
Latin America	973 4400 Tex	280; 305	260	18;21
Asia Pacific	973C 4500 Tex / 973CX1 2200 Tex	280	265	18

Technical Characteristics

LINEAR WEIGHT OF ROVING (TEX)	YIELDS (YD/LB)	LOSS ON IGNITION (%) ISO 1887:1995
2200/4400/4500	207/110	1.88

Packaging and Labeling

Each bobbin is protected by a plastic film (Tack-Pak®). Please do not remove film during use. Creel-Pak® packaging is available upon request.

Each bobbin has a self-adhesive identification label, showing the product reference and the production date. Each pallet has at least one identification label detailing the product reference, pallet net and gross weights, production date and pallet production code. The packaging system is designed to allow short term stacking of two pallets. When stacking two-high, care should be taken to correctly and smoothly place the top pallet. It is recommended to use a plywood plate between the two pallets in order not to damage the lower pallet.

MANUFACTURING REGION	PRODUCT	DOFF Ø (MM/IN)	PALLET DIM LxWxH (CM/IN)	LAYERS PER PALLET	DOFFS PER LAYER	NUMBER OF ENDS	PALLET NET WEIGHT (KG/LB)
North America	973 4500 Tex	280; 305; 355 / 11; 12; 14	142 x 109 x 119 / 56 x 43 x 47	4	12	1 to 16	1470/3,240
Latin America	973 4400 Tex	280; 305	129 x 97 x 120	4	12	1 to 12	1000
			115 x 115 x 120	4	16	1 to 16	1150
Asia Pacific	973C 4500 Tex 973CX1 2200 Tex	280	115 x 115 x 95	3	16	1 to 16	864

Storage

Unless otherwise specified, it is recommended to store glass fiber products in a cool, dry area. Ideal conditions are at a temperature between 10 °C and 35 °C and a relative humidity between 35% and 85%. The glass fiber products must remain in their original packaging material until the point of usage. If the storage temperature is below 15 °C, it is recommended that the product be stored in the workshop, within its original packaging, at least 24 hours prior to use to help prevent condensation. The packaging is not waterproof. Be sure to protect the product from the weather and other sources of water. When stored properly, there is no known shelf life to the product, and retesting is advised after three years from the initial production date to ensure optimum performance.

**MAKE
MORE
POSSIBLE™**

Americas

One Owens Corning Parkway
Toledo, Ohio, USA 43659
1-800-GET-PINK™

Europe

166 Chaussée De La Hulpe
B-1170 Brussels, Belgium
+32 3 674 8211

Asia Pacific

40/F, Pudong Kerry Parkside,
115 Fang Dian Road, Pudong,
Shanghai, 201204, China
+86-21-61019666

This information and data contained herein is offered solely as a guide in the selection of product. We believe this information to be reliable but do not guarantee its applicability to the user's process or assume any responsibility or liability arising out of its use or performance. The user agrees to be responsible for thoroughly testing any application of the product to determine its suitability. Because of numerous factors affecting results, we make no warranty of any kind, express or implied, including those of merchantability and fitness for a particular purpose. Statements in this publication shall not be construed as representations or warranties or as inducements to infringe on any patent or violate any law, safety code, or insurance regulation. We reserve the right to modify this document without prior notice.

Pub. No. 10010491. 973 & 973CX1 Product Data Sheet. December 2025. English. © 2026 Owens Corning. All Rights Reserved.