



P244 MULTI-END ROVING

Where consistent processing is key

P244 multi-end roving represents a robust solution for reinforcing light weight and high stiffness composite materials through demanding chopping conditions.

- ✔ P244 product is made from Advantex® glass strands.
- ✔ It is compatible with unsaturated polyester, vinyl ester, epoxy resins and polyurethane resins.

Product Benefits



Excellent Processability

- The product shows easy unwinding and chopping with negligible static build-up or fuzz, leading to excellent fiber distribution.
- Excellent fiber distribution enables the chopped strand layers to remain open and thus allows great wet through and impregnation.



High And Consistent Part Stiffness

- The resulting process efficiency provides consistent stiffness and integrity to the composite part.



Enhanced Service Life

- Advantex® glass helps fight corrosion, enhancing service life compared to standard E-glass.

Application

P244 product is designed to provide optimal performance in the reinforcement of headliners or gypsum boards. Also, it can be used as an input for the production of glass fabrics and complexes.



Technical Characteristics

LINEAR WEIGHT OF ROVING (TEX)	YIELDS (YD/LB)	LOSS ON IGNITION (%) ISO 1887:1995
2400	207	0.80
4800	103	0.80

Availability & Packaging

The product is available worldwide. Other Tex may be available upon request.

MANUFACTURING REGION	PRODUCT	LAYERS PER PALLET	DOFFS PER LAYER	NUMBER OF ENDS	PALLET NET WEIGHT (KG/LB)
Europe Latin America North America Asia Pacific	P244 2400/4800 Tex	4	12	4 or 12	1100/2,425
		4	16	4 or 16	1280/2,822

Each pallet can be packaged in bulk or Creel-Pak® packaging format. Pallets are stretch-wrapped for load stability and for protection during transport. All individual packages are wrapped with Tack-Pak® packaging to aid package run-out and transfer. More information is available in the Customer Acceptance Standards.

Labeling

Each doff has a self-adhesive identification label showing the product description, net weight and production date. Each pallet has at least two identification labels detailing the product reference, pallet net and gross weights, production date and pallet production code.

Storage

Unless otherwise specified, it is recommended to store glass fiber products in a cool, dry area. Ideal conditions are at a temperature between 10 °C and 35 °C and a relative humidity between 35% and 85%. The glass fiber products must remain in their original packaging material until the point of usage. If the storage temperature is below 15 °C, it is recommended that the product be stored in the workshop, within its original packaging, at least 24 hours prior to use to help prevent condensation. The packaging is not waterproof. Be sure to protect the product from the weather and other sources of water. When stored properly, there is no known shelf life to the product, and retesting is advised after three years from the initial production date to ensure optimum performance.

**MAKE
MORE
POSSIBLE™**

Americas

One Owens Corning Parkway
Toledo, Ohio, USA 43659
1-800-GET-PINK™

Europe

166 Chaussée De La Hulpe
B-1170 Brussels, Belgium
+32 3 674 8211

Asia Pacific

40/F, Pudong Kerry Parkside,
115 Fang Dian Road, Pudong,
Shanghai, 201204, China
+86-21-61019666

This information and data contained herein is offered solely as a guide in the selection of product. We believe this information to be reliable but do not guarantee its applicability to the user's process or assume any responsibility or liability arising out of its use or performance. The user agrees to be responsible for thoroughly testing any application of the product to determine its suitability. Because of numerous factors affecting results, we make no warranty of any kind, express or implied, including those of merchantability and fitness for a particular purpose. Statements in this publication shall not be construed as representations or warranties or as inducements to infringe on any patent or violate any law, safety code, or insurance regulation. We reserve the right to modify this document without prior notice.

Pub. No. 10011202-A. P244 Product Data Sheet. December 2025. English. © 2026 Owens Corning. All Rights Reserved.