



NO-WRAP FIBERGLAS™ PIPE INSULATION FIBERGLASS INSULATION

Owens Corning® No-Wrap Fiberglas™ pipe insulation is molded of heavy-density resin-bonded inorganic glass fibers that come in one-piece, 36-inch-long (914 mm), hinged sections. The insulation is tailored to fit for copper, iron, PVC, and other polymer pipe applications.

Features

- Insulation is tailored to fit with:
 - a flexible core to compress over copper and some small-bore iron, PVC, and polymer pipes and fittings, saving time by eliminating the need to fillet
 - a rigid core for fast and easy fabrication on larger pipes
- This product meets the performance requirements of ASTM C547 Type I with a maximum temperature of 850°F (454°C), however can be used up to a maximum operating temperature of 1,000°F (538°C) with heat-up schedule.
- The product does not contain Polybromodiphenyl ethers (PBDE) (penta-, octa-, or deca-brominated diphenyl)
- UL Labeled for Flame Spread Index of 0 or less and Smoke Developed Index of 0, and is fully building code compliant

Standards, Codes Compliance

- ASTM C547 Type I, Mineral Fiber Pipe Insulation
- ASTM C585, Inner and Outer Diameters of Thermal Insulation for Nominal Sizes of Pipe and Tubing
- NFPA 90A and 90B
- ASTM C795, Thermal Insulation for Use in Contact with Austenitic Stainless Steel¹
- Nuclear Regulatory Commission Guide 1.36, Non-Metallic Thermal Insulation¹
- MIL-PRF-22344E, Insulation, Pipe, Thermal, Fibrous Glass
- MIL-DTL-32585, Insulation, Thermal and Acoustic, Fibrous Glass; Type I; Form 4; Facing A
- MIL-DTL-24244D (Ships) Insulation Material with Special Corrosion, Chloride, and Fluoride Requirements¹
- U.S. Coast Guard 164.109/70/0 Non-Combustible
- NFPA 90A and 90B

¹ Preproduction qualification testing complete and on file. Chemical analysis of each production lot required for total conformance. Certification needs to be specified at time of order.

Physical Properties

PROPERTY	TEST METHOD	VALUE
Density (size dependent)	ASTM C302	3.5 to 5.5 pcf
Operating Temperature Range ³	ASTM C411	0°F to 1,000°F (-18°C to 538°C)
Water Vapor Sorption	ASTM C1104	Less than 5% by weight
Corrosion to Steel	ASTM C1617	Meets Requirements
Surface Burning Characteristics ²	UL 723, ASTM E84, or CAN/ULC-S102	Flame Spread 0 Smoke Developed 0

² The surface burning characteristics of these products have been determined in accordance with UL 723, ASTM E84, or CAN/ULC-S102. Values are reported to the nearest 5 rating.

³ With heat-up schedule when operating temperatures between 850°F and 1,000°F.

Applications

- Used to insulate iron, copper, PVC, and other polymer pipes with operating temperatures between 0°F (-18°C) to 1,000°F (538°C) in commercial & institutional buildings and industrial facilities
- When temperatures are above 650°F (454°C), maximum installed insulation thickness shall be no greater than 6 inches as a single layer or nested
- Rated per ASTM C547 Type I, Grade A — Insulation can be installed on in-service/hot pipes with an operating temperature up to 850°F (454°C); when application temperatures are between 850°F (454°C) and 1,000°F (538°C), thermal properties follow ASTM C547 Type I, and the heat-up procedure detailed in Pub. No. 10021355 should be followed
- When installed outdoors, an additional weather-protective jacket is required
- No-Wrap is intended for field installation with jacketing appropriate to the vapor control, damage, or corrosion-resistance requirements of the application

Thermal Conductivity

MEAN TEMPERATURE °F	k Btu-in/hr-ft²-°F	MEAN TEMPERATURE °C	λ W/m-°C
50	0.22	10	0.032
75	0.23	25	0.034
100	0.24	50	0.037
150	0.27	100	0.043
200	0.29	125	0.047
250	0.32	150	0.051
300	0.35	175	0.056
350	0.39	200	0.062
400	0.43	225	0.068
450	0.48	250	0.075
500	0.54	275	0.082

Apparent thermal conductivity values determined in accordance with ASTM practice C1045 with data obtained by ASTM Test Method C335. Values are nominal, subject to normal testing and manufacturing tolerances.

Thickness to Prevent Surface Condensation^{3,4}

AMBIENT TEMPERATURE		RELATIVE HUMIDITY	SYSTEM OPERATING TEMPERATURES						
°F	°C		35°F	(2°C)	45°F	(7°C)	55°F	(13°C)	
110	(43)	70%	1	(25)	1	(25)	1	(25)	
		80%	1½	(38)	1½	(38)	1½	(38)	
		90%	3½	(89)	3½	(89)	3	(76)	
100	(38)	70%	1	(25)	1	(25)	1	(25)	
		80%	1½	(38)	1½	(38)	1	(25)	
		90%	3½	(89)	3	(76)	2½	(64)	
90	(32)	70%	1	(25)	1	(25)	1	(25)	
		80%	1½	(38)	1	(25)	1	(25)	
		90%	3½	(89)	3	(76)	2½	(64)	
80	(27)	80%	1½	(38)	1	(25)	1	(25)	
		90%	3	(76)	2½	(64)	2	(51)	
70	(21)	80%	1	(25)	1	(25)	1	(25)	
		90%	2½	(64)	2	(51)	1	(25)	

3 Calculations estimated using NAIMA 3E Plus version 4.0 software. Fixed design conditions: Steel Horizontal Piping, 16" NPS, 0 mph wind speed, Outer Surface Jacket Emittance of 0.9.
4 Thermal conductivity values used in these calculations are subject to normal manufacturing tolerances.

Availability

Our Fiberglas™ pipe insulation portfolio is available in thicknesses up to 5 inches with inside diameters of up to 36 inches. Contact your local Owens Corning area sales manager for product availability.

Refer to Fiberglas™ Pipe Insulation Sizing Manual for more information: Pub No. 10018078.

Installation

Ambient application temperatures are from 25°F (-4°C) to 110°F (43°C).

For complete installation instructions and recommendations, see "Fiberglas™ Pipe Insulation Installation Instructions" (Pub. No. 10021355).

Environmental and Sustainability

Owens Corning is a worldwide leader in building material systems, insulation, and composite solutions, delivering a broad range of high-quality products and services. Owens Corning is committed to driving sustainability by delivering solutions, transforming markets, and enhancing lives. More information can be found at www.owenscorning.com.

Certifications and Sustainable Features

- Certified by SCS Global Services to contain an average of 53% recycled glass content, 31% pre-consumer, and 22% post-consumer.
- Environmental Product Declaration (EPD) has been certified by SCS Global Services
- Health Product Declaration (HPD).



Disclaimer of Liability

Technical information contained herein is furnished without charge or obligation and is given and accepted at recipient's sole risk. Because conditions of use may vary and are beyond our control, Owens Corning makes no representation about, and is not responsible or liable for, the accuracy or reliability of data associated with particular uses of any product described herein. SCS Global Services provides independent verification of recycled content in building materials and verifies recycled content claims made by manufacturers. For more information, visit www.SCSglobalservices.com.

Notes

For additional information, refer to the Safe Use Instruction Sheet (SUIS) found in the SDS Database via <http://sds.owenscorning.com>.

OWENS CORNING INSULATING SYSTEMS, LLC
ONE OWENS CORNING PARKWAY
TOLEDO, OH 43659 USA
1-800-GET-PINK®
www.owenscorning.com