



METRIC FIBERGLAS™ PIPE INSULATION FIBERGLASS INSULATION

Owens Corning® Metric Fiberglas™ pipe insulation is molded of heavy-density resin-bonded inorganic glass fibers that come in one-piece, 36-inch-long (914 mm), hinged sections. The insulation is tailored to fit for copper and iron pipe applications. Sections can be ordered as factory-applied SSL II® with ASJ Max, or as unjacketed No-Wrap.

Features

- ASJ Max is an all-service jacket with a polymer film exterior surface that is smooth, durable, cleanable, wrinkle-resistant, resists water staining, and doesn't support mold or mildew growth.¹
- ASJ Max can resist short durations of water exposure that may occur during construction.
- SSL II® Positive Closure System is an advanced double adhesion that fastens and installs with no need for staples or mastic.
- Insulation is tailored to fit with:
 - a flexible core to compress over copper and some small-bore iron pipes and fittings, saving time by eliminating the need to fillet.
 - a rigid core for fast and easy fabrication on larger pipes.
- This product meets the performance requirements of ASTM C547 Type I with a maximum temperature of 850°F (454°C), however can be used up to a maximum operating temperature of 1,000°F (538°C) with heat-up schedule.
- The product does not contain Polybromodiphenyl ethers (PBDE) (penta-, octa-, or deca-brominated diphenyl).

¹ ASJ Max jacket does not support mold growth as tested in accordance with ASTM C1338.

Standards, Codes Compliance

- ASTM C547, Mineral Fiber Pipe Insulation: Type I
- ASTM C585, Inner and Outer Diameters of Thermal Insulation for Nominal Sizes of Pipe and Tubing (Outer diameter only)
- ASTM F2389, Pressure-rated Polypropylene (PP) Piping System (Inner diameter dimensions)
- ASTM C1136, Flexible Low Permeance Vapor Retarders for Thermal Insulation: Types I, II, III, IV, X
- UL Labeled for Flame Spread Index of 25 or less and Smoke Developed Index of 50, and is fully building code compliant
- UL Listed and Labeled for use over PVC and other polymer pipes; UL Category BSMP
- ASTM C795, Thermal Insulation for Use in Contact with Austenitic Stainless Steel²
- Nuclear Regulatory Commission Guide 1.36, Non-Metallic Thermal Insulation²
- MIL-PRF-22344E, Insulation, Pipe, Thermal, Fibrous Glass
- MIL-DTL-32585, Type I, Form 4, Facing A
- MIL-DTL-24244D (Ships) Insulation Material with Special Corrosion, Chloride, and Fluoride Requirements²
- U.S. Coast Guard 164.109/70/0 Noncombustible (No-Wrap only). See No-Wrap Fiberglas™ Pipe Insulation Data Sheet for more information: Pub. No. 10022794
- NFPA 90A and 90B

² Preproduction qualification testing complete and on file. Chemical analysis of each production lot required for total conformance. Certification needs to be specified at time of order.

Physical Properties

PROPERTY	TEST METHOD	VALUE
Density (size dependent)	ASTM C302	3.5 to 5.5 pcf
Operating Temperature Range	ASTM C411	0°F to 1,000°F (-18°C to 538°C) ³
Water Vapor Sorption	ASTM C1104	Less than 5% by weight
Corrosion to Steel	ASTM C1617	Meets Requirements
Jacket Temperature Limitation	ASTM C1136	-20°F to 150°F (-29°C to 66°C)
Jacket Permeance	ASTM E96, Proc. A	0.01 perm
Burst Strength, min	ASTM D774/D774M	100 psi
Composite Surface Burning Characteristics ⁴	UL 723, ASTM E84, or CAN/ULC-S102	Flame Spread 25 Smoke Developed 50
Composite Surface Burning Characteristics ⁴	UL 723, ASTM E84, or CAN/ULC-S102	Flame Spread 0 Smoke Developed 0

³ With heat-up schedule when operating temperatures between 850°F and 1,000°F.

⁴ The surface burning characteristics of these products have been determined in accordance with UL 723, ASTM E84, or CAN/ULC-S102. Values are reported to the nearest 5 rating.

Applications

- Used to insulate iron, copper, PVC and other polymer pipes with operating temperatures between 0°F (-18°C) to 1,000°F (538°C) in commercial & institutional buildings, and industrial facilities
- When temperatures are above 650°F (454°C), maximum installed insulation thickness shall be no greater than 6" as a single layer or nested
- Rated per ASTM C547, Type I, Grade A — Pipe insulation can be installed on in-service/hot pipes with an operating temperature up to 850°F (454°C); When operating temperatures will be between 850°F (454°C) and 1,000°F (538°C), a heat-up schedule needs to be followed per the Installation Instructions, Pub. No. 10021355

Thermal Conductivity

MEAN TEMPERATURE °F	k Btu·in/hr·ft²·°F	MEAN TEMPERATURE °C	λ W/M·°C
50	0.20	10	0.029
75	0.21	25	0.031
100	0.22	50	0.034
150	0.25	100	0.041
200	0.28	125	0.044
300	0.33	150	0.048
400	0.41	175	0.053
500	0.49	200	0.058
550	0.55	225	0.063
600	0.60	250	0.069
650	0.67	300	0.082
700	0.74	350	0.098

Apparent thermal conductivity values determined in accordance with ASTM practice C1045 with data obtained by ASTM Test Method C335. Values are nominal, subject to normal testing and manufacturing tolerances.

Thickness to Prevent Surface Condensation^{5,6}

AMBIENT TEMPERATURE		RELATIVE HUMIDITY	SYSTEM OPERATING TEMPERATURES					
°F	°C		35°F	(2°C)	45°F	(7°C)	55°F	(13°C)
110	(43)	70%	1	(25)	1	(25)	1	(25)
		80%	1½	(38)	1½	(38)	1½	(38)
		90%	3½	(89)	3½	(89)	3	(76)
100	(38)	70%	1	(25)	1	(25)	1	(25)
		80%	1½	(38)	1½	(38)	1	(25)
		90%	3½	(89)	3	(76)	2½	(64)
90	(32)	70%	1	(25)	1	(25)	1	(25)
		80%	1½	(38)	1	(25)	1	(25)
		90%	3½	(89)	3	(76)	2½	(64)
80	(27)	80%	1½	(38)	1	(25)	1	(25)
		90%	3	(76)	2½	(64)	2	(51)
70	(21)	80%	1	(25)	1	(25)	1	(25)
		90%	2½	(64)	2	(51)	1	(25)

5 Calculations estimated using NAIMA 3E Plus version 4.0 software. Fixed design conditions: Steel Horizontal Piping, 16" NPS, 0 mph wind speed, Outer Surface Jacket Emittance of 0.9.
6 Thermal conductivity values used in these calculations are subject to normal manufacturing tolerances.

Acoustic – Insertion Loss in dB per ASTM E1222

Fiberglas™ Pipe Insulation with ASJ Max and SSL II®

FREQUENCY (HZ)	AT 1" THICKNESS	AT 2" THICKNESS
	INSERTION LOSS (dB)	INSERTION LOSS (dB)
315	-3	-2
400	2	0
500	1	0
630	3	1
800	0	-3
1000	6	8
1250	6	7
1600	10	13
2000	11	13
2500	16	20
3150	18	23
4000	19	23
5000	18	22

Availability

Our Fiberglas™ pipe insulation portfolio is available in thicknesses up to 2 inches with inside diameters of 20 mm up to 315 mm. Contact your local Owens Corning area sales manager for product availability.

Refer to Pipe Insulation Sizing Manual for more information (Pub. No. 10018078).

Installation

Ambient application temperatures are from 25°F (-4°C) to 110°F (43°C).

For complete installation instructions and recommendations, see "Fiberglas™ Pipe Insulation Installation Instructions" (Pub. No. 10021355).

Environmental and Sustainability

Owens Corning is a worldwide leader in building material systems, insulation, and composite solutions, delivering a broad range of high-quality products and services. Owens Corning is committed to driving sustainability by delivering solutions, transforming markets, and enhancing lives. More information can be found at www.owenscorning.com.

Certifications and Sustainable Features

- Certified by SCS Global Services to contain an average of 53% recycled glass content, 31% pre-consumer and 22% post-consumer.
- For faced products: GREENGUARD certified products are certified to GREENGUARD standards for low chemical emissions into indoor air during product usage. For more information, visit ul.com/gg.
- Environmental Product Declaration (EPD) has been certified by SCS Global Services.
- Health Product Declaration® (HPD) available for ASJ Max Fiberglas™ Pipe Insulation with SSL II® Closure and No-Wrap Fiberglas™ Pipe Insulation.



Disclaimer of Liability

Technical information contained herein is furnished without charge or obligation and is given and accepted at recipient's sole risk. Because conditions of use may vary and are beyond our control, Owens Corning makes no representation about, and is not responsible or liable for, the accuracy or reliability of data associated with particular uses of any product described herein. SCS Global Services provides independent verification of recycled content in building materials and verifies recycled content claims made by manufacturers. For more information, visit www.SCSglobalservices.com.

Notes

For additional information, refer to the Safe Use Instruction Sheet (SUIS) found in the SDS Database via <http://sds.owenscorning.com>.

OWENS CORNING INSULATING SYSTEMS, LLC
ONE OWENS CORNING PARKWAY
TOLEDO, OH 43659 USA
1-800-GET-PINK®
www.owenscorning.com