



4066 MULTI-END ROVING

Optimized panel surface appearance

4066 multi-end roving represents an ideal solution for demanding applications requiring high quality surface finish in continuous sheet production.

✔ Produced with Advantex® corrosion resistance E-CR glass.

✔ Compatible with unsaturated polyester resins.

FOR DEMANDING CONTINUOUS SHEET PRODUCTION APPLICATIONS

Product Benefits



Excellent Processability

- Easy unwinding and chopping, flat lay-down, and uniform dispersion with low fuzz and static.
- Easy choppability and splitting for excellent fiber distribution and laydown.



Enhanced Performance And Surface Aesthetics

- Better wet-out allows higher glass loading because of excellent wet-through and impregnation.
- Excellent fiber distribution for smooth surface aspect and consistent finish behind gel coat.



Enhanced Service Life

- Advantex® glass helps fight corrosion, enhancing service life compared to standard E-glass.

Applications

4066 glass reinforcement is designed to be chopped for the continuous production of recreational vehicle body parts.



Technical Characteristics

LINEAR WEIGHT OF ROVING (TEX)	YIELDS (YDS/LB)	LOSS ON IGNITION (%) ISO 1887:1995
2400	207	0.88
4800	103	0.85

Availability & Packaging

Each pallet can be packaged in Creel-Pak® packaging format. Pallets are stretch-wrapped for load stability and for protection during transport. All individual packages are wrapped with Tack-Pak® packaging to aid package run-out and transfer. More information is available in the Customer Acceptance Standards.

MANUFACTURING REGION	PRODUCT	LAYERS PER PALLET	DOFFS PER LAYER	NUMBER OF ENDS	PALLET NET WEIGHT (KG/LB)
North América	4066 2400 Tex Small Doffs	4	12	12	1,088/2,400
	4066 4800 Tex Small Doffs	3	16	4	868/1,914

Labeling

Each doff has a self-adhesive identification label showing the product description, net weight, and production date. Each pallet has at least two identification labels detailing the product reference, pallet net and gross weights, production date, and pallet production code.

Storage

Unless otherwise specified, it is recommended to store glass fiber products in a cool, dry area. Ideal conditions are at a temperature between 10 °C and 35 °C and a relative humidity between 35% and 85%. The glass fiber products must remain in their original packaging material until the point of usage. If the storage temperature is below 15 °C, it is recommended that the product be stored in the workshop, within its original packaging, at least 24 hours prior to use to help prevent condensation. The packaging is not waterproof. Be sure to protect the product from the weather and other sources of water. When stored properly, there is no known shelf life to the product, and retesting is advised after three years from the initial production date to ensure optimum performance.

**MAKE
MORE
POSSIBLE™**

US & Canada

2790 Columbus Road
Building 70
Granville, Ohio, USA 43023
+1 866 2GET GLAS

Europe

767 Quai Des Allobroges
Chambery
Rhone-Alpes 73000, France
+33 4 79 75 55 52

Asia Pacific

Room 301C+304,
1188 Minsheng Road,
Pudong, Shanghai
201705, China
+86 21 8010 3596

This information and data contained herein is offered solely as a guide in the selection of product. We do not guarantee its applicability to the user's process or assume any responsibility or liability arising out of its use or performance. The physical and chemical properties of this product represent typical, average values obtained in accordance with stated test methods and are subject to normal manufacturing variations. The user agrees to be responsible for thoroughly testing any application of the product to determine its suitability. Because of numerous factors affecting results, we make no warranty of any kind, express or implied, including those of merchantability and fitness for a particular purpose. Statements in this publication shall not be construed as representations or warranties or as inducements to infringe any patent or violate any law, safety code or insurance regulation. We reserve the right to modify this document without prior notice.

Pub. No. 10023408. 4066 Product Data Sheet. December 2025. English. © 2026 OC. All Rights Reserved.