



The walls in this building have been professionally insulated with

Owens Corning® PROPINK® Complete Blown in Insulation System

(Job Site Address)

Name _____

Address _____

City _____ State _____ Zip _____

Owens Corning® PROPINK® Complete Blown in Insulation system

Owens Corning Insulating Systems, LLC will accept no responsibility when the product is not installed in accordance with the product label. Stated R-value is provided by installing the required number of bags at a thickness not less than the labeled minimum thickness. Installation of the required number of bags may yield more than the specified minimum thickness. Failure by the installer to provide both the required bags and at least the minimum thickness will result in lower insulation R-value.

The PROPIINK® Complete Blown in Insulation System includes:

PROPIINK® L77 loose fill insulation, PROPIINK® Complete non-woven fabric and INSPECT-R® Gauge Density Gauge. Installation guideline can be found on Owens Corning Pub. No. 101133-F.

Wall Coverage Chart

Coverage charts are based on a nominal net bag weight of 32 lbs.

| R-value | Framing | Minimum Initial Installed Thickness (Inches) | Installed Density (lbs per cu. ft.) | Maximum Coverage Per Bag (sq. ft.) | Minimum Bags Per 1000 sq. ft. | Minimum Weight (lbs per sq. ft.) |
|---------|---------|--|-------------------------------------|------------------------------------|-------------------------------|----------------------------------|
| 14 | 2x4 | 3.5 | 1.25 | 87.8 | 11.4 | 0.364 |
| 15 | 2x4 | 3.5 | 1.45 | 75.7 | 13.2 | 0.423 |
| 16 | 2x4 | 3.5 | 2.20 | 49.9 | 20.1 | 0.642 |
| 22 | 2x6 | 5.5 | 1.25 | 55.9 | 17.9 | 0.573 |
| 23 | 2x6 | 5.5 | 1.35 | 51.7 | 19.3 | 0.619 |
| 24 | 2x6 | 5.5 | 1.75 | 40.0 | 25.0 | 0.802 |

2x4 Walls

Coverage charts are for Inspect-R® Gauge

| To reach an R-value of | You need a minimum average Inspect-R® reading (W.C.) of | With a density (PCF) of |
|------------------------|---|-------------------------|
| 14 | 0.40 | 1.25 |
| 15 | 0.62 | 1.45 |
| 16 | 1.47 | 2.20 |

| To reach an R-value of | You need a minimum average Inspect-R® reading (W.C.) of | With a density (PCF) of |
|------------------------|---|-------------------------|
| 23 | 0.51 | 1.35 |
| 24 | 0.96 | 1.75 |

Owens Corning® glass fiber blanket and loosefill thermal insulations, when installed per the manufacturers' coverage charts and recommendations, will provide the labeled R-value.

THE FOLLOWING DENSITY READINGS WERE RECORDED FOR THE WALL IN THIS BUILDING

Room _____ Location _____ 2x4 2x6 Inches of water column _____ Density _____ R- Value _____
Room _____ Location _____ 2x4 2x6 Inches of water column _____ Density _____ R- Value _____
Room _____ Location _____ 2x4 2x6 Inches of water column _____ Density _____ R- Value _____
Room _____ Location _____ 2x4 2x6 Inches of water column _____ Density _____ R- Value _____
Room _____ Location _____ 2x4 2x6 Inches of water column _____ Density _____ R- Value _____
Room _____ Location _____ 2x4 2x6 Inches of water column _____ Density _____ R- Value _____

SQFT Wall Area _____ Total Number of Bags used _____

Contractor _____ Date _____ Builder _____ Date _____
Company _____ *(Signature)* Company _____ *(Signature)*
Address _____ Address _____
Phone _____ Phone _____



OWENS CORNING INSULATING SYSTEMS, LLC
ONE OWENS CORNING PARKWAY
TOLEDO, OHIO, USA 43659
1-800-GET-PINK®
www.owenscorning.com

Pub. No. 10023457. Printed in U.S.A. March 2019. The color PINK is a registered trademark of Owens Corning. © 2019 Owens Corning Insulating Systems, LLC. All Rights Reserved.