



# SE4121 SINGLE-END ROVING

## Robust performance in harsh processing environments

Type 30<sup>®</sup> SE4121 single-end roving represents a compelling solution for Polypropylene Long Fiber Thermoplastics (LFT-G and D-LFT) applications where excellent mechanical properties and hydrolysis resistance are required.

✔ Produced with patented Advantex<sup>®</sup> corrosion resistant E-CR glass by Owens Corning.

✔ Compatible with Polyolefins: PP, PE and HDPE resin systems.

### Product Benefits



#### Compounding Line Efficiency

- No catenary and high resistance to fuzz generation equate to low cleanup & high machine efficiencies.



#### Mechanical Performance

- Optimal adhesion to the Polyolefin resin matrix provides excellent dry-as-molded mechanical properties and hydrolysis resistance.



#### Enhanced Service Life

- Advantex<sup>®</sup> glass helps fight corrosion, extends service life compared to standard E-glass.



#### Multi-Process Compatible

- Suitable for all D-LFT and LFT-G processes and choppable to desired length.



#### Excellent Impregnation & Dispersion

- Both D-LFT and LFT-G processes show excellent dispersion within the final parts.

### Application

The SE4121 product is designed for use in all LFT-G (compounded pellets) and D-LFT (direct compounding and molding) processes. It is used for the manufacturing of structural and semi-structural automotive applications including front-end modules, seat carriers and door modules, as well as a variety of consumer goods, appliances and power tools.

### Availability

TEX	YIELD	REGION AVAILABLE
13800	36	China
17600	28	North America
19200	26	EU, China, India

## Mechanical Properties

Data generated using production material SE 4121 2400 Tex (207 Yield).

PELLET (12 MM)	TENSILE STRENGTH (MPa)	FLEXURAL STRENGTH (MPa)	FLEXURAL MODULUS (MPa)
PP resin + Glass content 50%	189	282	11447

Test results will vary by Process and Formulation.

## Packaging

Rovings are available in a single-end internal-pull package. Each pallet weighs about 1 ton and can be packaged in bulk or Creel-Pak® packaging format. Pallets are stretch wrapped for load stability and for protection during transport. Full doffs are available in weights between 15 kg (33 lb) and 20 kg (44 lb), and can be packaged in bulk or Creel-Pak® format. All individual packages are wrapped with Tack-Pak® packaging to aid package run-out and transfer. More information is available in the Customer Acceptance Standards.

## Labeling

Each individual package is labeled with information including: product name, tex/yield, producing plant, and production date.

## Storage

Unless otherwise specified, it is recommended to store glass fiber products in a cool, dry area. The glass fiber products must remain in their original packaging material until the point of usage. The product should be stored in the workshop in its original packaging for 48 hours prior to its utilization, to allow it to reach the workshop temperature condition and prevent condensation, especially during the cold season. The packaging is not waterproof. Be sure to protect the product from the weather and other sources of water.

When stored properly, there is no known shelf life to the product, but retesting is advised after three years from the initial production date to ensure optimum performance.

**MAKE  
MORE  
POSSIBLE™**

### Americas

One Owens Corning Parkway  
Toledo, Ohio, USA 43659  
1-800-GET-PINK™

### Asia Pacific

40/F, Pudong Kerry Parkside,  
115 Fang Dian Road, Pudong,  
Shanghai, 201204, China  
+86-21-61019666

This information and data contained herein is offered solely as a guide in the selection of product. We believe this information to be reliable but do not guarantee its applicability to the user's process or assume any responsibility or liability arising out of its use or performance. The user agrees to be responsible for thoroughly testing any application of the product to determine its suitability. Because of numerous factors affecting results, we make no warranty of any kind, express or implied, including those of merchantability and fitness for a particular purpose. Statements in this publication shall not be construed as representations or warranties or as inducements to infringe on any patent or violate any law, safety code, or insurance regulation. We reserve the right to modify this document without prior notice.

Pub. No. 10023662-A. SE4121 Product Data Sheet. December 2025. English. © 2026 Owens Corning. All Rights Reserved.