



FOAMGLAS®

PITTSEAL® HI-TEMP LV RTV SEALANT



Description and Area of Application

PITTSEAL® HI-TEMP LV RTV sealant is a one-part, neutral cure, sealant formulated for use with FOAMGLAS® insulation systems. The lower viscosity of PITTSEAL® HI-TEMP LV RTV sealant enables the sealant to efficiently spread and seal FOAMGLAS® insulation in these systems. The sealant cures to an elastomeric solid at room temperature.

It is particularly suited for use in conjunction with FOAMGLAS® cellular glass insulation systems that require adhering or sealing FOAMGLAS® insulation to FOAMGLAS® insulation or adhering insulation to hot surfaces.

Type of Delivery and Storage

- 305 ml (10.3 fl. oz.) cartridges. Twelve (12) cartridges per carton.
- Store original, unopened containers in a cool, dry area.
- Protect unopened containers from water, heat and direct sunlight.
- Consult Safety Data Sheet for additional storage and handling information.

Coverage

Standard application of adhesive to FOAMGLAS® insulation:

- 305 ml (10.3 fl oz) cartridge:
880 cm² x 3 mm (136 in² x 1/8 inch) film
- 305 ml (10.3 fl oz) cartridge:
Will produce a bead ~ 7.3 m (~ 24 ft) in length and
~ 6.4 mm (~ 1/4 inch) in diameter

Field Application

Always read and understand information contained within product datasheets and safety datasheets before attempting to use this product. If you have questions regarding fitness of use of this product for a particular application, consult Owens Corning.

Substrate Preparation

All surfaces should be dry and free of dust, loose scale, oil, grease and frost.

Cellular Glass Application Guidelines

DO NOT thin. Apply with trowel, knife or caulking gun. Apply sufficient material to both surfaces and press surfaces together firmly to obtain a complete seal.

Cut nozzle to 6.4 mm (1/4 inch) or desired bead size. Apply 6.4 mm (1/4 inch) diameter beads of sealant in parallel every 10 cm (4 inches) to insulation and press to the substrate using a slight rotary motion.

Joints less than or equal to 3 mm (1/8 inch) are desirable. Do not use this or any other sealant to fill large voids from poor fitting insulation. The mating surfaces of the insulation should be rubbed together to obtain good fit before application of sealant.

If a coating is to be applied, remove excessive sealant flush with surface.

Cleanup and Disposal

Allow sealant to cure. Mechanically remove from surfaces.

Discard excess sealant and containers in accordance with local, state and federal regulations.

Limitations

- DO NOT use in applications where solvent odor could affect food taste or flavor.
- DO NOT use in areas subject to continuous immersion.

Typical Properties

PROPERTY ¹	TEST METHOD	SI	ENGLISH
Color			Red
Density		1.05 ± 0.02 kg/L	8.8 ± 0.2 lb/gal
Application Temperature Material Surface		28 ± 7°C -7 ± 45°C	82 ± 12°F 19 ± 81°F
Service Temperature ² Maximum, Intermittent Maximum, Continuous Minimum		232°C 204°C -150°C	450°F 400°F -238°F
Tensile Strength	ASTM D412	1.21 ± 0.17 MPa	175 ± 25 psi
Elongation at Break	ASTM D412		300 ± 50%
Durometer Hardness	ASTM D661 (Shore A)		20 ± 2
Cure Time/Rate Skin Over Tack-Free Rate		12 minutes at 25°C @ 50% RH 25 minutes at 25°C @ 50% RH 3.2 mm per 30 hours	12 minutes at 77°F @ 50% RH 25 minutes at 77°F @ 50% RH 1/8 inch per 30 hours
Volatile Organic Content (VOC), Maximum Less Water and Exempt ³		≤ 36 g/L	≤ 0.30 lb/gal
Water Vapor Permeability ⁴	ASTM E96 (Wet Cup) ASTM E96 (Dry Cup) EN12086:1997	0.28 ng / Pa·s·m 0.32 ng / Pa·s·m 0.29 ng / Pa·s·m	0.19 perm-in 0.22 perm-in 0.20 perm-in

1. Properties are subject to change. Consult Owens Corning.

2. Service temperature limits are derived from laboratory evaluation of the product. Variations in substrates, loading conditions, or other external factors may further limit service temperature. Always consult FOAMGLAS® Insulation System Specification for suitability for use recommendations for a specific application.

3. Sealant is certified to meet the general requirements for VOC emissions of SCAQMD Rule 1168, October 6, 2017 Adhesive and Sealant Applications, as analyzed by the methods specified in Rule 1168.

4. Material tested as cured disk.

Sealant meets stainless steel service requirements of ASTM C795 and NRC Regulatory Guide 1.36.

For additional information on FOAMGLAS® Insulation Systems, please contact Owens Corning or visit us at www.foamglas.com.

The information contained herein is accurate and reliable to the best of our knowledge. But, because Pittsburgh Corning, LLC has no control over installation workmanship, accessory materials or conditions of application, NO EXPRESSED OR IMPLIED WARRANTY OF ANY KIND, INCLUDING THOSE OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, IS MADE as to the performance of an installation containing Owens Corning products. In no event shall Pittsburgh Corning, LLC be liable for any damages arising because of product failure, whether incidental, special, consequential or punitive, regardless of the theory of liability upon which any such damages are claimed. Pittsburgh Corning, LLC provides written warranties for many of its products, and such warranties take precedence over the statements contained herein.

Technical information contained herein is furnished without charge or obligation and is given and accepted at recipient's sole risk. Because conditions of use may vary and are beyond our control, Owens Corning makes no representation about and is not responsible or liable for the accuracy or reliability of data associated with particular uses of any product described herein.

Industrial & Commercial Sales

Americas
+1 800 327 6126

Asia-Pacific

Singapore: +65 9635 9184
China: +86 (0) 21 6101 7179
Japan: +81 3 6365 4307

Europe, Middle East & Africa
+32 13 661 721

Technical Services

Americas & Asia-Pacific
+1 800 327 6126

foamglastechnical@owenscorning.com

Europe, Middle East & Africa

+32 13 611 468
industry.tech@owenscorning.com



PITTSBURGH CORNING, LLC
ONE OWENS CORNING PARKWAY
TOLEDO, OHIO 43659 USA

Toll Free + 1 800 327 6126
www.foamglas.com