



SE4850 SINGLE-END ROVING

Redefining performance in D-LFT PP

Type 30[®] SE4850 single-end roving represents a compelling solution for polypropylene in direct long fiber thermoplastics (D-LFT) applications where improved performance and manufacturing economics is required.

✔ Produced with patented Advantex[®] corrosion resistant E-CR glass by Owens Corning.

✔ Compatible with polyolefins: PP, PE, and HDPE resin systems.

SPECIFICALLY FOR USE IN DIRECT LONG FIBER THERMOPLASTIC (D-LFT) PROCESSES

Product Benefits



- Improved resistance to fuzz generation for easier processing and improved housekeeping
- Reduced strand stiffness for easier splaying
- Increased lubricity for lower strand tension
- Improved splice tensile strength for enhanced package-to-package transfer and improved line efficiencies



- Outstanding compatibility with PP for better wet-out and dispersion
- Optimized adhesion to PP to meet or exceed all mechanical performance needs

Up to
80% reduction
in fuzz generation

Up to
40% improvement
in glass dispersion

Up to
80% increase
in splice strength

Up to
80% increase
in impact performance

Data Sources: Mech. prop.: 30% Glass Content; compression molding, Fraunhofer Institute Molding
Owens Corning Internal Testing—Granville, Q4 2014
Fuzz: vs. other DLFT reinforcements, Owens Corning internal tests—Ibaraki
Glass dispersion: vs. Competitor product, Owens Corning Granville and Ibaraki Testing
Splice strength: vs. Owens Corning historic standard, Owens Corning internal tests—Ibaraki


Application

SE4850 product is designed for use in polypropylene direct LFT (D-LFT) processes where the glass strand is fed directly into the compounding extruder. It is used for the manufacturing of structural and semi-structural complex automotive applications such as front-end modules, seat carriers, and door modules while also being used in a variety of non-automotive applications for consumer goods, building materials, and recreational vehicles.

Availability & Technical Characteristics

TEX	YIELD	FILAMENT DIAMETER (μ)	LOSS ON IGNITION (%)	MOISTURE (% MAX)	MANUFACTURING REGION
2400	207	17	0.40%	0.05%	North America, Europe, Asia Pacific
4400	113	23	0.40%	0.05%	Asia Pacific
4800	103	24	0.40%	0.05%	Asia Pacific
4800	103	17	0.40%	0.05%	Asia Pacific

Mechanical Properties



Outstanding mechanical properties deliver up to **80% increase** in impact strength

Potential for reduced wall thickness and/or reduced use of coupling agent for comparable end use performance

Data source: 30% glass content; compression molding. Fraunhofer institute molding; Owens Corning internal Testing, Granville, Q4 2014.

Packaging

PALLET DIMENSIONS

PACKAGING	PALLET HEIGHT (CM)	PALLET LENGTH (CM)	PALLET WIDTH (CM)	PALLET WEIGHT (NET, KG)	PACKAGES PER PALLET	NUMBER OF LAYERS
No Tube	~ 125	115	115	~ 1200	64	4
No Tube	~ 97	115	115	~ 900	48	3
Thicker Tube	~ 200	115	115	~ 900	48	3

Rovings are available in a single-end internal-pull package. Each pallet weighs about 1 ton and can be packaged in bulk or Creel-Pak® packaging format. Pallets are stretch wrapped for load stability and for protection during transport. Full doffs are available in weights between 15 kg (33 lb) and 20 kg (44 lb) and can be packaged in bulk or Creel-Pak® format. All individual packages are wrapped with Tack-Pak® packaging to aid package run-out and transfer. Packaging may vary by region. More information is available in the Customer Acceptance Standards.

Labeling

Each individual package is labeled with information including product name, Tex/yield, producing plant, and production date.

Storage

Unless otherwise specified, it is recommended to store glass fiber products in a cool, dry area. The glass fiber products must remain in their original packaging material until the point of usage. The product should be stored in the workshop in its original packaging for 48 hours prior to its utilization to allow it to reach the workshop temperature condition and prevent condensation, especially during the cold season. The packaging is not waterproof. Be sure to protect the product from the weather and other sources of water.

When stored properly, there is no known shelf life to the product, but retesting is advised after three years from the initial production date to ensure optimum performance.

**MAKE
MORE
POSSIBLE™**

Americas

One Owens Corning Parkway
Toledo, Ohio, USA 43659
1-800-GET-PINK™

Europe

166 Chaussée De La Hulpe
B-1170 Brussels, Belgium
+32 3 674 8211

Asia Pacific

40/F, Pudong Kerry Parkside,
115 Fang Dian Road, Pudong,
Shanghai, 201204, China
+86-21-61019666

India

7th Floor, Alpha Building,
Hiranandani Gardens
Powai, Mumbai- 400076
Landline No – +91 22 66681700

This information and data contained herein is offered solely as a guide in the selection of product. We believe this information to be reliable but do not guarantee its applicability to the user's process or assume any responsibility or liability arising out of its use or performance. The user agrees to be responsible for thoroughly testing any application of the product to determine its suitability. Because of numerous factors affecting results, we make no warranty of any kind, express or implied, including those of merchantability and fitness for a particular purpose. Statements in this publication shall not be construed as representations or warranties or as inducements to infringe on any patent or violate any law, safety code, or insurance regulation. We reserve the right to modify this document without prior notice.

Pub. No. 10023895. Performax® SE4850 Product Data Sheet. December 2025. English. © 2026 Owens Corning. All Rights Reserved.