



# HIGHER PERFORMANCE COMPOSITES

Introducing higher performance composites by Owens Corning – OC HP has more modulus, more benefits, more opportunities. This new higher performance glass provides a boost in mechanical properties enhancing part performance or cost optimization through redesign. The compatibility and processing of Owens Corning’s sizing chemistries are directly transferable to higher performance to easily leverage into your existing operations and designs.

## OC HP — NEXT LEVEL COMPOSITES

### Product Benefits



#### PULTRUSION

Reduce the weight of pultruded parts by up to 8% by using higher modulus glass, saving material cost.




#### TELECOM

Central strength members can be made 8% lighter, enabling increased fiber optic capacity in the cable.



#### REBAR

Higher modulus can enable fiberglass rebar with modulus up to 70 GPa on straight bars. Properties previously unattainable on bent bars can now be achieved.




#### FILAMENT WINDING

Improve performance by up to 15% in axial tensile strength for helically wound pipe compared to reference products.



#### LONG FIBER THERMOPLASTICS

Reduce the weight of parts for automotive applications by up to 9%.



#### MUFFLERS

The glass can be used in high temperature muffler applications due to an annealing point increase of 25-30°C compared to current products.

### Applications



## More Strength and Modulus than Advantex®

FIBER AND BULK GLASS PROPERTIES	TEST METHOD	UNIT	E-GLASS	ADVANTEXTM E-CR GLASS	OC HP
Fiber Density (predicted)	Proprietary	g/cm <sup>3</sup>	2.60-2.62	2.63	2.59
Refractive Index (bulk annealed)	Proprietary		1.562-1.565	1.567	1.557

MECHANICAL PROPERTIES	TEST METHOD	UNIT	E-GLASS	ADVANTEXTM E-CR GLASS	OC HP
Pristine Fiber Tensile Strength, 22 °C	Proprietary	MPa	3815-3830	4050	4650
Young's Modulus, 22 °C	Proprietary	GPa	78-79	82	89.5
Elongation at Break	ASTM D3822	%	3	3	4

## Corrosion Resistance

SOAKING SOLUTION	ADVANTEXTM	COMPETITOR 1	COMPETITOR 2	COMPETITOR 3	OC HP
NaOH pH=12.88	X	X	X	✓	✓
10% HCl	✓	✓	✓	X	✓
10% H <sub>2</sub> SO <sub>4</sub>	✓	✓	✓	X	✓

Glass was tested using a dry tensile method based on ASTM D578 before and after soaking in corrosive solutions for 32 days. Passing is defined as retention of ≥75% of starting strength.

### Americas

#### Owens Corning Composite Materials, LLC.

One Owens Corning Parkway  
Toledo, Ohio, USA 43659  
1-800-GET-PINK®

### Europe

#### European Owens Corning Fiberglas Sprl.

166 Chaussée de la Hulpe  
B-1170 Brussels  
Belgium  
+32 3 674 8211

### Asia Pacific

#### Owens Corning Shanghai Regional Headquarters

40/F, Pudong Kerry Parkside,  
115 Fang Dian Road, Pudong,  
Shanghai, 201204, China  
+86-21-6101 9666

<https://www.owenscorning.com/composites> | [Composites@owenscorning.com](mailto:Composites@owenscorning.com)

This information and data contained herein is offered solely as a guide in the selection of product. We believe this information to be reliable, but do not guarantee its applicability to the user's process or assume any responsibility or liability arising out of its use or performance. The user agrees to be responsible for thoroughly testing any application of the product to determine its suitability. Because of numerous factors affecting results, we make no warranty of any kind, express or implied, including those of merchantability and fitness for a particular purpose. Statements in this publication shall not be construed as representations or warranties or as inducements to infringe any patent or violate any law, safety code or insurance regulation. We reserve the right to modify this document without prior notice.