


M524-C64 **DRY-LAID** GLASS NONWOVEN

M524-C64 consists of spun 'C' glass rod made from 12.5 µm of randomly orientated semi-continuous filament glass fibers. The glass fiber veil is bonded by a modified styrene acrylic resin and is designed to be used as a surfacing tissue for GRP laminates.

FOR SURFACING APPLICATIONS

Product Benefits

- Excellent conformability.
- Great wet-out capability.



Technical Characteristics (Nominal Values)

PROPERTY	TEST METHOD	SPECIFICATION	NORMAL LIMITATIONS	
			MAX.	MIN.
Area Weight (g/m²)	PTS-L-002	30	33	27
Binder Content (%)	PTS-L-003	7.5	9	6
Thickness (mm)	PTS-L-007	0.29	0.33	0.25



Americas

Owens Corning Composite Materials, LLC.

One Owens Corning Parkway Toledo, Ohio, USA 43659 1-800-GET-PINK®

Europe

European Owens Corning Fiberglas Sprl.

166 Chaussée de la Hulpe B-1170 Brussels Belgium +32 3 674 8211

Asia Pacific

Owens Corning Shanghai Regional Headquarters

40/F, Pudong Kerry Parkside, 115 Fang Dian Road, Pudong, Shanghai, 201204, China +86-21-6101 9666

https://www.owenscorning.com/composites | Composites@owenscorning.com

This information and data contained herein is offered solely as a guide in the selection of product. We believe this information to be reliable, but do not quarantee its applicability to the user's process or assume any responsibility or liability arising out of its use or performance. The user agrees to be responsible for thoroughly testing any application of the product to determine its suitability. Because of numerous factors affecting results, we make no warranty of any kind, express or implied, including those of merchantability and fitness for a particular purpose. Statements in this publication shall not be construed as representations or warranties or as inducements to infringe any patent or violate any law, safety code or insurance regulation. We reserve the right to modify this document without prior notice