



ST2070LS SINGLE-END ROVING

Match emission regulations

Type 30® ST2070LS single-end roving is specifically designed for use in the Silentex® Exhaust filling process. ST2070LS was developed to match stringent global emission regulations on particulate matter. The product meets emission standards for EURO 6d, China 6b, and Japan 2018 standards for Tier 3, LEV III, and Bharat VI.

- ✓ Robust solution to meet demanding acoustic requirements, support increasing engine temperatures, and lower overall cost of silencers as well as reduced weight, volume, and back pressure.
- ✓ Produced with patented Advantex® corrosion resistant E-CR glass by Owens Corning.

FOR GLOBAL NOISE CONTROL SOLUTIONS

Product Benefits

- Enhanced Service Life & Durability**
 - Advantex® glass provides longer service life with a high temperature composition specifically engineered for use in the Owens Corning Silentex® process, which minimizes process interruptions and ensures overall product efficiency.
 - Fibers remain continuous and resist blowout with five times the strength of basalt wool and twice the strength of E-glass under the most corrosive conditions.
 - Glass annealing point ≥ 720 °C (according to ASTM C336).
 - Based on the available data and experience, it is recommended to use ST2070LS at a maximum continuous glass temperature of ~740 °C.
- Excellent Processing**
 - Smooth run-out from lower drag across contact points produces less fuzz, resulting in smoother parts, less clean-up, and improved machine efficiencies.
- Consistent Performance**
 - Narrow and consistent fiber diameter distribution for reliable sound absorption for reduced fill density compared to basalt preforms or needle felt.

Application

ST2070LS is designed for use in the manufacture of cost-effective automotive muffler systems with optimal durability and acoustic performance.



Availability & Packaging

PRODUCT	AVE. FILAMENT DIAMETER (μ): ISO 1888	LINEAR DENSITY (TEX): ISO 1889	LOSS ON IGNITION (%): ISO 1887	MOISTURE (%): ISO 3344	MANUFACTURING REGION
ST2070LS	24	7000 \pm 560; 4800 \pm 400	0.1 (max 0.2)	\leq 0.2	Americas, Asia Pacific

MANUFACTURING REGION	PRODUCT (TEX)	ROVING	PACKAGING	PALLET WIDTH (MM)	PALLET LENGTH (MM)	PALLET HEIGHT (MM)	PALLET NET WEIGHT (KG)
Yuhang (China)	ST2070LS 7000 or 4800	Advantex® low LOI	Creel-Pak® 1end and Bulk	1150	1150	1000	-1215
Yuhang (China)	ST2070LS 7000 or 4800	Advantex® low LOI	Creel-Pak® 1end and Bulk	900	1150	1000	-1095
L'Ardoise (France)	ST2070LS 7000	Advantex® low LOI	Creel-Pak® 1end and 2end Bulk	800	1200	1000	-850

Each pallet can be packaged in bulk or Creel-Pak® packaging format. Pallets are stretch wrapped for load stability and for protection during transport. All individual packages are wrapped with Tack-Pak® packaging to aid package run-out and transfer. More information is available in the Customer Acceptance Standards.

Labeling

Each individual package is labeled with information including: product name, Tex/yield, producing plant, and production date.

Storage

Unless otherwise specified, it is recommended to store glass fiber products in a cool, dry area. The glass fiber products must remain in their original packaging material until the point of usage. The product should be stored in the workshop, within its original packaging, 48 hours prior to its utilization to allow it to reach the workshop temperature condition and prevent condensation. The packaging is not waterproof. Be sure to protect the product from the weather and other sources of water. When stored properly, there is no known shelf life to the product, but retesting is advised after three years from the initial production date to ensure optimum performance.

**MAKE
MORE
POSSIBLE™**

Europe
166 Chaussée De La Hulpe
B-1170 Brussels, Belgium
+32 3 674 8211

Asia Pacific
40/F, Pudong Kerry Parkside,
115 Fang Dian Road, Pudong,
Shanghai, 201204, China
+86-21-61019666

This information and data contained herein is offered solely as a guide in the selection of product. We believe this information to be reliable but do not guarantee its applicability to the user's process or assume any responsibility or liability arising out of its use or performance. The user agrees to be responsible for thoroughly testing any application of the product to determine its suitability. Because of numerous factors affecting results, we make no warranty of any kind, express or implied, including those of merchantability and fitness for a particular purpose. Statements in this publication shall not be construed as representations or warranties or as inducements to infringe on any patent or violate any law, safety code, or insurance regulation. We reserve the right to modify this document without prior notice.

Pub. No. 10024056. ST2070LS Product Data Sheet. December 2025. English. © 2026 Owens Corning. All Rights Reserved.