



P249 MULTI-END ROVING

Optimal results at high speed

P249 multi-end roving is a compelling solution designed to provide optimal use for long fiber injection (LFI) applications.

✔ Produced with patented Advantex® corrosion resistant E-CR glass by Owens Corning.

✔ Compatible with polyurethane resin systems.

FOR LONG FIBER INJECTION APPLICATIONS

Product Benefits



Excellent Processing

- Proprietary sizing enables optimal processing in LFI applications with: low static and no fuzz, easy chopping without long fiber cuts, and excellent runnability with smooth unwinding, even at high speeds.



Enhanced Service Life

- Compared to standard E-glass, Advantex® glass helps with enhanced service life in applications facing corrosion.

Application

P249 can be used for LFI processes to produce parts for agricultural, recreational vehicles, trucks, or construction machinery.



Technical Characteristics

LINEAR WEIGHT OF ROVING (TEX)	LOSS ON IGNITION (%)	MOISTURE CONTENT (%)
ISO 1889	ISO 1887	ISO 3344
2400/4800	1.40	≤0.20

Availability & Packaging

P249 is produced in the EU but available worldwide on request.

Each doff of P249 is protected by a bag, made of shrink-wrap polyethylene, which should not be removed when it is used, and each bag is identified by an individual label.

Air splice package is available on request.

MANUFACTURING REGION	PRODUCT	LAYERS PER PALLET	DOFFS PER LAYER	TOTAL NUMBER OF DOFFS	NUMBER OF ENDS	PALLET NET* WEIGHT (KG)
Europe	EC 2400/4800 P249	3/4	16	48/64	1 - 2 - 4 - 16	884/1312

* Add 35 to 45 kg to obtain gross weight.

Each pallet can be packaged in bulk or Creel-Pak® packaging format. Pallets are stretch wrapped for load stability and for protection during transport. All individual packages are wrapped with Tack-Pak® packaging to aid package run-out and transfer. More information is available in the Customer Acceptance Standards.

Labeling

Each doff has a self-adhesive identification label showing the product description, net weight, and production date. Each pallet has at least two identification labels detailing the product reference, pallet net and gross weights, production date, and pallet production code.

Storage

Unless otherwise specified, it is recommended to store glass fiber products in a cool, dry area. Ideal conditions are at a temperature between 10 °C and 35 °C and a relative humidity between 35% and 85%. The glass fiber products must remain in their original packaging material until the point of usage. If the storage temperature is below 15 °C, it is recommended that the product be stored in the workshop, within its original packaging, at least 24 hours prior to use to help prevent condensation. The packaging is not waterproof. Be sure to protect the product from the weather and other sources of water. When stored properly, there is no known shelf life to the product, and retesting is advised after three years from the initial production date to ensure optimum performance.

**MAKE
MORE
POSSIBLE™**

Europe
166 Chaussée De La Hulpe
B-1170 Brussels, Belgium
+32 3 674 8211

This information and data contained herein is offered solely as a guide in the selection of product. We believe this information to be reliable but do not guarantee its applicability to the user's process or assume any responsibility or liability arising out of its use or performance. The user agrees to be responsible for thoroughly testing any application of the product to determine its suitability. Because of numerous factors affecting results, we make no warranty of any kind, express or implied, including those of merchantability and fitness for a particular purpose. Statements in this publication shall not be construed as representations or warranties or as inducements to infringe on any patent or violate any law, safety code, or insurance regulation. We reserve the right to modify this document without prior notice.

Pub. No. 10024128. P249 Product Data Sheet. December 2025. English. © 2026 Owens Corning. All Rights Reserved.