



K247 MULTI-END SPUN ROVING

Increased shearing performance



K247 multi-end spun roving is specifically designed to provide extra reinforcement in the transversal direction.

- ✔ Strands are structured into loops to form the roving, providing maximum strand strength.
- ✔ Produced with patented Advantex® corrosion resistant E-CR glass by Owens Corning.
- ✔ Compatible with unsaturated polyester, vinyl ester, and epoxy resin systems.

FOR PULTRUSION, WEAVING, AND FILAMENT WINDING

Product Benefits



Excellent Processing

- Features easy unwinding and excellent package run-out for uniform dispersion with low fuzz and static, which means less cleanup and better machine efficiencies.
- Ideal ability to take up complex shapes of profiles by extrusion.
- Provides even glass/resin distribution, resulting in excellent surface aspect in the finished product.



Enhanced Service Life & Durability

- Compared to standard E-glass, Advantex® glass helps with enhanced service life in applications facing corrosion.

Application

K247 spun roving is especially designed for applications requiring additional reinforcement in the transversal direction such as pultrusion of profiles and weaving for shipbuilding.



Technical Characteristics

LINEAR WEIGHT OF ROVING (TEX) ISO 1889	LOSS ON IGNITION (%) ISO 1887	MOISTURE CONTENT (%) ISO 3344
1800/2800/4000	0.6	<0.15

Availability & Packaging

Each K247 roving is protected and packed into a polyamide plastic bag and identified with an individual label.

MANUFACTURING REGION	PRODUCT	DOFF Ø INT / EXT (MM)	PALLET DIMENSIONS L x W (CM)	LAYERS PER PALLET	DOFFS PER LAYER	PALLETS APPROXIMATE FIBERGLASS WEIGHT* (KG)
Europe	K247 1800	75/220	114 x 114	4	25	11.5
	K247 2400	75/280		4	16	11.5
	K247 4800					19.0

*Add 50 kg for the gross weight

Labeling

Each doff has a self-adhesive identification label showing the product description, net weight, and production date. Each pallet has at least two identification labels detailing the product reference, pallet net and gross weights, production date, and pallet production code.

Storage

Unless otherwise specified, it is recommended to store glass fiber products in a cool, dry area. Ideal conditions are at a temperature between 10 °C and 35 °C and a relative humidity between 35% and 85%. The glass fiber products must remain in their original packaging material until the point of usage. If the storage temperature is below 15 °C, it is recommended that the product be stored in the workshop, within its original packaging, at least 24 hours prior to use to help prevent condensation. The packaging is not waterproof. Be sure to protect the product from the weather and other sources of water. When stored properly, there is no known shelf life to the product, and retesting is advised after three years from the initial production date to ensure optimum performance.

**MAKE
MORE
POSSIBLE™**

Europe
166 Chaussée De La Hulpe
B-1170 Brussels, Belgium
+32 3 674 8211

This information and data contained herein is offered solely as a guide in the selection of product. We believe this information to be reliable but do not guarantee its applicability to the user's process or assume any responsibility or liability arising out of its use or performance. The user agrees to be responsible for thoroughly testing any application of the product to determine its suitability. Because of numerous factors affecting results, we make no warranty of any kind, express or implied, including those of merchantability and fitness for a particular purpose. Statements in this publication shall not be construed as representations or warranties or as inducements to infringe on any patent or violate any law, safety code, or insurance regulation. We reserve the right to modify this document without prior notice.

Pub. No. 10024292. K247 Product Data Sheet. December 2025. English. © 2026 Owens Corning. All Rights Reserved.