



SE 4805 HP SINGLE-END ROVING

Higher mechanical performance

Type30® SE 4805 HP single-end roving is specifically designed as a higher performance solution for compounders seeking increased productivity through improved processing and handling characteristics, and excellent compatibility in Polypropylene LFT applications in manufacturing facilities certified to ISO 9001.

✓ Produced with patented higher performance glass by Owens Corning (OC HP), the product provides superior mechanical properties with the excellent corrosion resistance expected from our Advantex® formulations.

✓ Compatible with Polyolefins: PP, PE, and HDPE resin systems.

Product Benefits



Lightweighting

- 9% weight reduction by reducing LFTP part thickness – ideal for automotive lightweighting.
- 2.5% potential weight reduction in LFTP compound.



Superior Glass Dispersion/Increased Part Strength

- Outstanding compatibility with Polyolefins, enabling better wet-out, uniform glass dispersion, and potential higher glass loading.
- Optimized adhesion to the polymer matrix, offering excellent mechanical properties to meet stringent end-use requirement.



Enhanced Service Life

- Like Advantex glass, HP glass helps fight corrosion, enhancing service life compared to standard E-Glass.

For Compounders

2.5%

potential weight reduction in compound.



For OEMs

9%

weight reduction by reducing part thickness.



Application

SE 4805 HP is an advanced member of the Type 30® roving family and specially designed for polypropylene long-fiber thermoplastic applications with LFT-G (pultrusion), D-LFT, and CFRT (Continuous Fiber Reinforced Thermoplastics), for the manufacturing of structural and semi-structural automotive applications, including front-end modules, seat carriers, and door modules, as well as a variety of consumer goods, appliances, and power tools. SE4805 HP is also optimized for use in CFRT (Continuous Fiber Reinforced Plastic) tapes for structural applications where the performance characteristics of a continuous unidirectional glass reinforcement can significantly improve end-use performance.

Mechanical Properties & Performance Testing

TENSILE STRENGTH	TENSILE MODULUS	FLEXURAL STRENGTH	FLEXURAL MODULUS	IMPACT — NOTCHED CHARPY I	IMPACT — UNNOTCHED CHARPY
+13%	+9%	+10%	+8%	+19%	+14%

Note: Data generated using production SE4805 HP and standard SE 4805 HP for comparison. Both products were 2400 tex with 17 µm fibers, and were tested at 30% glass loading in a standard PP resin formulation.

Availability & Technical Characteristics

TEX	YIELD	FILAMENT DIAMETER (µ)	LOSS ON IGNITION (%)	MOISTURE (% MAX)	MANUFACTURING REGION
2400	207	17	0.35%	0.05%	Asia Pacific
1200	413	17	0.35%	0.05%	Asia Pacific

Packaging

Rovings are available in 20 kg single-end, internal pull. Pallet dimensions 16x4 rovings. Pallets are stretch-wrapped for load stability. Pallets are available in bulk pallet packaging format, and are manufactured in India for export globally.

Labeling

Each individual package is labeled with information including product name, tex/yield, producing plant, and production date.

Storage

Unless otherwise specified, it is recommended to store glass fiber products in a cool, dry area. The glass fiber products must remain in their original packaging material until the point of usage. The product should be stored in the workshop in its original packaging for 48 hours prior to its utilization, to allow it to reach the workshop temperature condition and prevent condensation, especially during the cold season. The packaging is not waterproof. Be sure to protect the product from the weather and other sources of water.

When stored properly, there is no known shelf life to the product, but retesting is advised after three years from the initial production date to ensure optimum performance.

ISO Standards

SE 4805 single-end roving is manufactured in conformity with the following standards: ISO 2797, NF B38151 and DIN 61855.

**MAKE
MORE
POSSIBLE™**

Americas

One Owens Corning Parkway
Toledo, Ohio, USA 43659
1-800-GET-PINK™

Europe

166 Chaussée De La Hulpe
B-1170 Brussels, Belgium
+32 3 674 8211

Asia Pacific

40/F, Pudong Kerry Parkside,
115 Fang Dian Road, Pudong,
Shanghai, 201204, China
+86-21-61019666

India

7th Floor, Alpha Building,
Hiranandani Gardens
Powai, Mumbai- 400076
Landline No – +91 22 66681700

This information and data contained herein is offered solely as a guide in the selection of product. We believe this information to be reliable but do not guarantee its applicability to the user's process or assume any responsibility or liability arising out of its use or performance. The user agrees to be responsible for thoroughly testing any application of the product to determine its suitability. Because of numerous factors affecting results, we make no warranty of any kind, express or implied, including those of merchantability and fitness for a particular purpose. Statements in this publication shall not be construed as representations or warranties or as inducements to infringe on any patent or violate any law, safety code, or insurance regulation. We reserve the right to modify this document without prior notice.

Pub. No. 10024446. SE4805 HP Product Data Sheet. December 2025. English. © 2026 Owens Corning. All Rights Reserved.