



OPTISPRAY® PRO MULTI-END ROVING

Better productivity and aesthetics

OptiSpray® PRO multi-end roving represents a compelling solution for fabricators that want to save time and improve cosmetic appearance.

- ✔ Multi-end gun roving reinforcement using Advantex® glass fiber, which combines the electrical and mechanical properties of traditional E-glass with the acid corrosion-resistance of E-CR glass.
- ✔ Advantex® glass roving has a sizing system designed to provide optimal performance for spray-up applications where fast wet-out, increased productivity, and manufacturing speed is preferred.

FOR OPTIMAL PRODUCTIVITY AND AESTHETICS

Product Benefits



Increased Productivity

- OptiSpray® PRO Roving is offered in a unique 4-high doff pallet configuration weighing ~2700 lb (1254 kg) per pallet. This design increases productivity by requiring less pallet turnovers and less time moving material by fewer employees.



Reduced Cost

- Higher glass loading with optimal resin consumption reduces the amount of expensive resin required.



Improved Aesthetics

- Reduction in fiber print, improved short-term and long-term waviness, and improved B-side cosmetics.



Fast Wet-Out

- Designed to provide optimal performance for spray-up applications where fast wet-out speed is preferred; great performance in various types of part complexities.



Packaging To Reduce Waste And Increase Floorspace

- The optional 4-high pallet design increases the amount of fiberglass material in the standard pallet footprint by 33%, enabling producers to fit more pounds within a distribution center, on a truck during delivery, and in the manufacturing site with no impact to floor space.

Up to
21% ↑↑
increase in
productivity.*

*Third-party external evaluation of a Marine structural liner showed up to a 21% reduction in time/ft² versus worst-performing fiberglass option.

Application

OptiSpray® PRO Roving can be used in a variety of spray-up applications, including boats, truck caps, heavy-truck body parts, bath tubs, showers, spas, tanks, pools, and applications with complex molds or sharp curvatures.

Technical Characteristics

LINEAR WEIGHT OF ROVING (TEX)	YIELD (YD/LB)	LOSS ON IGNITION (%) ISO 1887:1995
2400	207	1.25
3000	165	1.25

Availability & Packaging

- Each OptiSpray® PRO doff is protected by a tack-wrap polythene film and identified by an individual label; please do not remove film during use.
- Creel-Pak® and customer-specific packaging may be available upon request.

PRODUCT	DOFF Ø (MM)	PALLET DIMENSIONS LxW (CM)	LAYERS PER PALLET	DOFFS PER LAYER	TOTAL NUMBER OF DOFFS	CREEL-PAK®	PALLETS APPROX. FIBERGLAS
						NUMBER OF ENDS	WEIGHT* (kg)
OptiSpray® PRO Rov. Creel-Pak® 4E 2400/3000	277	114 x 114	3	16	48	4	941
OptiSpray® PRO Rov. Creel-Pak® 2E 2400/3000	277	114 x 114	3	16	48	2	941
			4		64		1254
OptiSpray® PRO Rov. Close Top® 2400	303	38 x 51 in 96.5 x 129.5 cm	4	12	48	Individual Boxes	1104

Labeling

Each doff has a self-adhesive identification label showing the product reference and the production date.

Each pallet has five identification labels detailing the product reference, pallet net and gross weights, production date, and pallet production code.

Storage

Unless otherwise specified, it is recommended to store glass fiber products in a cool, dry area. Ideal conditions are at a temperature between 10 °C and 35 °C and a relative humidity between 35% and 85%. The glass fiber products must remain in their original packaging material until the point of usage. If the storage temperature is below 15 °C, it is recommended that the product be stored in the workshop, within its original packaging, at least 24 hours prior to use to help prevent condensation. The packaging is not waterproof. Be sure to protect the product from the weather and other sources of water. When stored properly, there is no known shelf life to the product, and retesting is advised after three years from the initial production date to ensure optimum performance.

**MAKE
MORE
POSSIBLE™**

Americas
One Owens Corning Parkway
Toledo, Ohio, USA 43659
1-800-GET-PINK™

Asia Pacific
40/F, Pudong Kerry Parkside,
115 Fang Dian Road, Pudong,
Shanghai, 201204, China
+86-21-61019666

This information and data contained herein is offered solely as a guide in the selection of product. We believe this information to be reliable but do not guarantee its applicability to the user's process or assume any responsibility or liability arising out of its use or performance. The user agrees to be responsible for thoroughly testing any application of the product to determine its suitability. Because of numerous factors affecting results, we make no warranty of any kind, express or implied, including those of merchantability and fitness for a particular purpose. Statements in this publication shall not be construed as representations or warranties or as inducements to infringe on any patent or violate any law, safety code, or insurance regulation. We reserve the right to modify this document without prior notice.

Pub. No. 10024566. OptiSpray® PRO Roving Product Data Sheet. December 2025. English. © 2026 Owens Corning. All Rights Reserved.