



ECOSTRAND® SINGLE-END ROVING

Designed
to perform



EcoStrand® Type 30® single-end roving has been designed to provide reliable shear strength and flexural properties in polyester and vinyl ester resin systems for pultrusion applications.

✓ Produced with Advantex® corrosion-resistant E-CR glass by Owens Corning.

✓ Compatible with polyester and vinyl ester resin systems (not recommended for epoxy).

FOR PULTRUSION APPLICATIONS

Product Benefits



Good Processing

- Fast, easy unwinding with smooth run-out for better efficiency.
- Uniform wet-out optimizes fabrication time and provides improved productivity.
- Low fuzz properties result in less downtime for clean-up, enabling higher efficiencies and lower manufacturing costs.



Good Mechanical Properties

- Sizing designed to provide very good shear strength and flexural properties in polyester and vinyl ester resin systems.
- Very good hydrolytic aging performance.



Enhanced Service Life

- Compared to standard E-glass, Higher Performance is an E-CR glass that provides longer service life in applications facing corrosion, and possesses high-fatigue properties to help qualify for wind energy.

Application

EcoStrand® is designed for industrial pultrusion applications, such as walkways, gratings, railings, ladders, cable trays, and pultruded sections of large structural profiles, including cooling towers and others.



Technical Characteristics

The following data were generated by evaluating EcoStrand® using unsaturated polyester resin systems. Sample preparation and fiber weight fraction were controlled to create comparable data.

Flexural strength
1120 MPA
ASTM D790

Interlaminar shear strength
44 MPA
(short beam strength)
Test method ASTM D2344

Availability & Packaging

EcoStrand® is available in India.

MANUFACTURING LOCATION	TEX	PACKAGE WEIGHT
Taloja	4800 Tex (24 μ)	20-25 kg

Labeling

Each individual package is labeled with information including product name, Tex/yield, producing plant, and production date.

Storage

Glass fiber products should be stored in a cool, dry area. The glass fiber products must remain in their original packaging material until use. The product should be stored in the workshop, within its original packaging, 48 hours prior to its utilization, to allow it to reach the workshop temperature condition and prevent condensation, especially during cold weather. The packaging is not waterproof. Be sure to protect the product from the weather and other sources of water. When stored properly, the product has no known shelf-life issues, but retesting is advised after three years from the initial production date to ensure optimum performance.

**MAKE
MORE
POSSIBLE™**

India
7th Floor, Alpha Building,
Hiranandani Gardens
Powai, Mumbai- 400076
Landline No – +91 22 66681700

This information and data contained herein is offered solely as a guide in the selection of product. We believe this information to be reliable but do not guarantee its applicability to the user's process or assume any responsibility or liability arising out of its use or performance. The user agrees to be responsible for thoroughly testing any application of the product to determine its suitability. Because of numerous factors affecting results, we make no warranty of any kind, express or implied, including those of merchantability and fitness for a particular purpose. Statements in this publication shall not be construed as representations or warranties or as inducements to infringe on any patent or violate any law, safety code, or insurance regulation. We reserve the right to modify this document without prior notice.

Pub. No. 10024641. EcoStrand® Product Data Sheet. December 2025. English. © 2026 Owens Corning. All Rights Reserved.