




ARCOTEX® 5326 COMPOSITE RESIN SYNERGY

ARCOTEX® 5326 has been specifically developed to be used with polyester and vinylester resins in corrosion-resistant applications.

- Produced with Owens Corning® Cem-FIL® AR-glass chemistry, ARCOTEX® fibers are designed for composite reinforcement.
- ARCOTEX® 5326 roving is treated with silane-based coupling agents, which allow a high level of performance to be obtained with resins and hardener systems in general use.
- High elastic modulus and tensile strength provides effective reinforcement.
- Designed to be highly resistant to corrosion in both acid and alkali environments.

FOR FILAMENT WINDING AND PULTRUSION APPLICATIONS

Product Benefits



Performance

- Corrosion-resistant glass
- Excellent performance in both acid and alkali media
- No static electricity



Processing

- Excellent unwinding
- Low level of fuzz
- Excellent wet-out characteristics

Applications

ARCOTEX® 5326 is designed mainly for use in filament winding and pultrusion, but is also suitable for weaving applications.



Technical Characteristics

LINEAR DENSITY OF ROVING (TEX) (ISO 1889:2009)	FILAMENT DIAMETER (µm) (ISO 1888)	LOSS ON IGNITION (%) (ISO 1887:1995)	MOISTURE (%) (ISO 3344:1997)
600	19	0.80	0.30 max.
1200	19	0.80	0.30 max.
2400	27	0.80	0.30 max.

- **Direct Roving**
- **Electrical Conductivity:** Very low
- **Specific Gravity:** 2.68 g/cm³
- **Material:** Alkali-resistant glass*
- **Softening Point:** 860°C–1,580°F
- **Chemical Resistance:** Very high
- **Modulus of Elasticity:** 72 GPa – 10 x 10⁶ psi
- **Tensile Strength:** >1,000 MPa – >145 x 10³ psi

* Our fibers are manufactured with high zirconia content in compliance with ASTM C1666/C1666/M-07 and EN 15422 and under the recommendations of PCI and GRCA.

Packaging & Storage

ARcoteX® 5326 rovings are protected by a shrink-wrap polythene film, open at the top, which should not be removed when the product is in use. Rovings are packed on pallets. ARcoteX® 5326 rovings should be stored away from heat and moisture, and in their original packaging. Optimum conditions are temperatures between 15°C and 35°C and humidity between 35% and 65%. If the product is stored at lower temperatures, it is advisable to condition it in the workshop for at least 24 hours before use, to prevent condensation.

Quality Standards

ARcoteX® 5326 fibers are manufactured under a quality management system approved to ISO 9001.

ARcoteX® fibers are not classified as dangerous by the Regulation 1272/2008/EC. For more information, please refer to our Safe Use Instruction Sheet.

CE-marking and Declaration of Performance as fibers for use in concrete and mortar through European Technical Assessment ETA 17/0169 for 600 and 1200 tex.

Verified Environmental Product Declaration according to ISO 14025 and EN 15804:2019 available upon request.



Americas

Owens Corning Composite Materials, LLC.
One Owens Corning Parkway
Toledo, OH 43659 USA
1-800-GET-PINK®

Europe

European Owens Corning Fiberglas Sprl.
166 Chaussée de la Hulpe
B-1170 Brussels
Belgium
+32 3 674 8211

Asia Pacific

Owens Corning Shanghai Regional Headquarters
40/F, Pudong Kerry Parkside,
115 Fang Dian Road, Pudong,
Shanghai, 201204, China
+86-21-6101 9666

<https://www.owenscorning.com/composites> | Composites@owenscorning.com

The information and data contained herein is offered solely as a guide in the selection of product. We believe this information to be reliable but do not guarantee its applicability to the user's process or assume any responsibility or liability arising out of its use or performance. The user agrees to be responsible for thoroughly testing any application of the product to determine its suitability. Because of numerous factors affecting results, we make no warranty of any kind, express or implied, including those of merchantability and fitness for a particular purpose. Statements in this publication shall not be construed as representations or warranties or as inducements to infringe on any patent or violate any law, safety code, or insurance regulation. We reserve the right to modify this document without prior notice.

Pub number: 10025221. ARcoteX® 5326_product data sheet. January 2022. English.

THE PINK PANTHER™ & © 1964–2022 Metro-Goldwyn-Mayer Studios Inc. All Rights Reserved. © 2022 Owens Corning. All Rights Reserved.