



LUXESTRAND™ 220

RELIABLE SMOOTH AND EVEN SURFACES

LuxeStrand™ 220 multi-end roving represents a compelling solution for headliner applications.

- Produced with Advantex® corrosion-resistant E-CR glass by Owens Corning.
- Compatible with polyester, vinyl ester, and polyurethane resin systems.

FOR HEADLINERS WHERE SURFACE ASPECT IS KEY

Product Benefits

Excellent Processability

- Designed for excellent processing at various line speeds, LuxeStrand™ 220 features easy unwinding and chopping, flat lay-down, and uniform dispersion with low fuzz and static.
- Excellent choppability yields cleaner machinery and less maintenance.

Excellent Surface Aspect

- Process benefits combined with desirable product design ensure smooth and even surfaces, and invisible glass fibers on finished parts.

Enhanced Service Life

- Advantex® glass helps fight corrosion, enhancing service life compared to standard E-glass.

Applications

LuxeStrand™ 220 is designed for headliner applications where surface aspect is key. The perfect glass opening and distribution ensure smooth surface and homogeneous thickness.



Technical Characteristics (Nominal Values)

LINEAR WEIGHT (TEX) (G/KM)	LOSS ON IGNITION (%)	MOISTURE (%)
ISO 1889:1997	ISO 1887:1995	ISO 3344:1997
2400	1.20	≤0.20

Availability & Packaging (Standard Reference)

PRODUCT (TEX)	LAYERS PER PALLET	DOFFS PER LAYER	NUMBER OF ENDS	PALLET NET WEIGHT (KG/LB)	MANUFACTURING REGION
LuxeStrand™ 220 (2400)	4	12	12	1,100/2,425	Europe

Different packaging options may be available upon request.

Labeling

Each doff has a self-adhesive identification label showing the product reference and the production date. Each pallet has at least one identification label detailing the product reference, pallet net and gross weights, production date, and pallet production code. The packaging system is designed to allow short-term stacking of two pallets. When stacking two-high, care should be taken to correctly and smoothly place the top pallet. It is recommended to use a plywood plate between the two pallets in order to not damage the lower pallet.

Storage

It is recommended to store glass fiber products in a cool, dry area. The glass fiber products must remain in their original packaging material until the point of usage; the product should be stored in the workshop, within its original packaging, 48 hours prior to its utilization, to allow it to reach the workshop temperature condition and prevent condensation, especially during the cold season. The packaging is not waterproof. Be sure to protect the product from the weather and other sources of water. When stored properly, there is no known shelf life to the product, but retesting is advised after two years from the initial production date to ensure optimum performance.



Americas

Owens Corning Composite Materials, LLC.
One Owens Corning Parkway
Toledo, OH 43659 USA
1-800-GET-PINK®

Europe

European Owens Corning Fiberglas Sprl.
166 Chausée de la Hulpe
B-1170 Brussels
Belgium
+32 3 674 8211

Asia Pacific

Owens Corning Shanghai Regional Headquarters
40/F, Pudong Kerry Parkside,
115 Fang Dian Road, Pudong,
Shanghai, 201204, China
+86-21-6101 9666

<https://www.owenscorning.com/composites> | Composites@owenscorning.com

This information and data contained herein is offered solely as a guide in the selection of product. We believe this information to be reliable but do not guarantee its applicability to the user's process or assume any responsibility or liability arising out of its use or performance. The user agrees to be responsible for thoroughly testing any application of the product to determine its suitability. Because of numerous factors affecting results, we make no warranty of any kind, express or implied, including those of merchantability and fitness for a particular purpose. Statements in this publication shall not be construed as representations or warranties or as inducements to infringe on any patent or violate any law, safety code, or insurance regulation. We reserve the right to modify this document without prior notice.