



# TURBOSPRAY® MULTI-END ROVING

## Increase productivity

**TURBOSPRAY® multi-end roving represents a premium roving solution for fabricators that want to improve productivity and aesthetics.**

✔ Multi-end gun roving reinforcement using Advantex® glass fiber, which combines the electrical and mechanical properties of traditional E-glass with the acid corrosion resistance of E-CR glass.

✔ TURBOSPRAY® has a sizing system designed to provide optimal performance for spray-up applications where fast wet-out, increased productivity, and improved surface finishes are preferred.

### PRODUCTIVE RESULTS WITH INCREASED VISUAL APPEAL

#### Product Benefits

- Fast Wet-Out**
  - Designed to provide optimal performance for spray-up applications where fast wet-out, productivity, and exceptional useability are needed within various types of part complexities. Owens Corning has observed up to 21% more productive results, based on time, compared to competitive fibers.
- Mechanical Performance**
  - The improved laydown and conformability around tight radii enable a user to maintain longer chop lengths to achieve optimized mechanical properties.
- Aesthetics**
  - TURBOSPRAY® offers improved long- and short-term waviness, which improves surface appearances and is verified through wavelength measurements.
- Reduced Cost**
  - Higher glass loading with optimal resin consumption reduces the amount of more costly resins.

#### Application

TURBOSPRAY® Roving can be used in a variety of spray-up applications, including boats, truck caps, heavy-truck body parts, bathtubs, showers, spas, tanks, pools, and applications with complex molds or sharp curvatures.

#### Technical Characteristics

LINEAR WEIGHT OF ROVING (TEX)	YIELD (YD/LB)	LOSS ON IGNITION (%) — NOMINAL ISO 1887
2400	207	1.25

## Availability & Packaging

- Each TURBOSPRAY® doff is protected by a tack-wrap polythene film and identified by an individual label;
- please do not remove film during use.
- Customer-specific packaging may be available upon request.

PRODUCT	DOFF DIAMETER (MM)	PALLET DIMENSIONS L X W (CM)	LAYERS PER PALLET	DOFFS PER LAYER	TOTAL NUMBER OF DOFFS	NUMBER OF ENDS	PALLETS APPROX. FIBERGLAS' (KG)
TURBOSPRAY® 2400 Creel-Pak® 2E	280	114 x 114	3	16	48	2	950

<sup>1</sup>Add approximately 30–40 kg to obtain pallet gross weight.

## Labeling

Each doff has a self-adhesive identification label showing the product reference and the production date.

Each pallet has five identification labels detailing the product reference, pallet net and gross weights, production date, and pallet production code.

## Storage

Unless otherwise specified, it is recommended to store glass fiber products in a cool, dry area. Ideal conditions are at a temperature between 10 °C and 35 °C and a relative humidity between 35% and 85%. The glass fiber products must remain in their original packaging material until the point of usage. If the storage temperature is below 15 °C, it is recommended that the product be stored in the workshop, within its original packaging, at least 24 hours prior to use to help prevent condensation. The packaging is not waterproof. Be sure to protect the product from the weather and other sources of water. When stored properly, there is no known shelf life to the product, and retesting is advised after three years from the initial production date to ensure optimum performance.

**MAKE  
MORE  
POSSIBLE™**

**Europe**  
166 Chaussée De La Hulpe  
B-1170 Brussels, Belgium  
+32 3 674 8211

This information and data contained herein is offered solely as a guide in the selection of product. We believe this information to be reliable but do not guarantee its applicability to the user's process or assume any responsibility or liability arising out of its use or performance. The user agrees to be responsible for thoroughly testing any application of the product to determine its suitability. Because of numerous factors affecting results, we make no warranty of any kind, express or implied, including those of merchantability and fitness for a particular purpose. Statements in this publication shall not be construed as representations or warranties or as inducements to infringe on any patent or violate any law, safety code, or insurance regulation. We reserve the right to modify this document without prior notice.

Pub. No. 10027083. TURBOSPRAY® Roving Product Data Sheet. December 2025. English. © 2026 Owens Corning. All Rights Reserved.