



# NATURAL-THERM<sup>®</sup> PRO



Natural-Therm<sup>®</sup> Pro is a closed cell, two-component spray polyurethane foam insulation with a low GWP blowing agent and a nominal 2.0 PCF in-place density. These products provide energy efficiency and air infiltration control as a high-performance building envelope insulation system. Natural-Therm<sup>®</sup> Pro offers a self-adhering, seamless insulation designed for use in residential and commercial building envelopes, including wall cavities, attics, crawl spaces, perimeter rim joists, cathedral ceilings, and garage ceilings.

## Features

- Low VOC<sup>1</sup>
- Low GWP Blowing Agent
- R-Value > 7 per inch
- Air Seal
- FEMA Class 5 Flood Resistance<sup>2</sup>
- Soil-Gas (Radon) Retarder

<sup>1</sup> www.ul.com/gg

<sup>2</sup> https://www.fema.gov/sites/default/files/2020-07/fema\_tb\_2\_rev1.pdf

## Standards, Codes Compliance

- ICC-ES AC308 Type I-IV and V-B
- Code Evaluation Report IAPMO UES ER-1005
- ASTM C1029 - Type II Compliant
- NFPA 285 commercial wall assembly fire performance
- NFPA 286 Appendix X
- Tested for Radon Resistance (NRC A1-023490)
- UL GREENGUARD GOLD
- ICC 1100

## Applications

- Walls (interior and exterior)
- Vented Attics
- Unvented Attics
- Ceilings
- Unvented Crawl Spaces
- Vented Crawl Spaces
- Rim Joists
- Floors
- Under Slab
- Foundation Walls

## Packaging, Storage, and Shelf Life

**A Component:** 55 US Gallons, Closed-Top Steel Drum – 500 lb. net wt.

**B Component:** 55 US Gallons, Closed-Top Steel Drum – 475 lb. net wt.

Store containers between 50°F and 80°F in a well-ventilated place. Keep the container tightly closed. Store locked up. Containers should be opened carefully to allow any pressure buildup to be vented safely while wearing full safety protection. Excessive venting of the B Component may result in higher density foam and reduced yield.

Shelf Life: 6 months when stored in the original unopened container at 50°F–80°F. Excessive low or high temperatures may decrease shelf life.

Processing: Drum temperatures should be conditioned to 70°F–80°F before application to ensure optimal viscosity and mixing.

## Thermal Resistance – R-Values

THICKNESS (INCHES)	°F*FT <sup>2</sup> *H/BTU
1	7.1
2	14
3.5	24
4	28
5	35
5.5	38
6	41
7	48
7.25	50
8	55
9	62
9.25	64
10	69

For SI: 1 inch = 25.4 mm, °F \*ft<sup>2</sup>\*h/Btu = 0.176 K\*m<sup>2</sup>/W

<sup>1</sup> R-values are calculated based on tested K values at 1-inch and 3.5-inch thickness for Natural-Therm<sup>®</sup> Pro Series.

## Equipment

The proportioning equipment must be manufactured specifically for heating, mixing, and spray application of polyurethane foam and be able to maintain 1:1 metering with a +/-2% variance and adequate main heating capacity to deliver heated and pressurized materials up to 150°F.

## Physical Properties

PROPERTY	TEST METHOD	VALUE
Thermal Resistance	See Table Below	
R-Value <sup>1</sup> (1 inch)	ASTM C518	7.1
R-Value <sup>1</sup> (3.5 inches)		24
Core Density	ASTM D1622	Nominal 2.0 PCF
Compressive Strength <sup>2</sup>	ASTM D1621	37 psi
Tensile Strength <sup>2</sup>	ASTM D1623	43 psi
Dimensional Stability	ASTM D2126	
158°F 97% RH (168 h)		-2.55%
Air Permeance (1 inch)	ASTM E2178	Meets criteria
Vapor Permeance (1 inch)	ASTM E96	1.54 perm
Air Infiltration (1 inch)	ASTM E283	Meets criteria
System Air Leakage	ASTM E2357	Pass
Water Infiltration	ASTM E331	Pass
Pull Adhesion	ASTM D4541	Pass
Crack Bridging	ASTM C1305	Pass
Fungi Resistance	ASTM C1338	Pass
Water Absorption	ASTM D2842	Pass
Closed Cell Content	ASTM D6226	> 90%
Spray-Applied Rigid Cellular Thermal Polyurethane Thermal Insulation	ASTM C1029	Type II Compliant

## FIRE TEST RESULTS<sup>3</sup>

Flame Spread	ASTM E84 (Complies with Class 1) <sup>3</sup>	< 25
Smoke Developed		< 450
Thermal Barrier <sup>4</sup>	NFPA 286	Pass with 14 mils (wet) DC 315 Pass with 14 mils (wet) No-Burn Plus ThB
Ignition Barrier <sup>4</sup>	NFPA 286 AC 377 Appendix X	Pass without an intumescent coating
Wall Assembly	NFPA 285	Pass – Type Class I-IV, V-B Construction

<sup>1</sup> R means the resistance to heat flow; the higher the value, the greater the insulation power. This insulation must be installed properly to get the marked R-value.

<sup>2</sup> Value at yield or 10% deflection, whichever occurs first.

<sup>3</sup> These laboratory tests are not intended to describe the hazards presented by this material under actual fire conditions.

<sup>4</sup> Reference IAPMO UES ER-1005 for guidance on maximum application thicknesses on vertical and horizontal surfaces.

## Safety and Handling

**Exposure** — Read and understand the Safety Data Sheet (SDS) for this product before use. Personnel must use appropriate respiratory, skin, and eye Personal Protective Equipment (PPE) when handling and applying polyurethane spray foam systems. Both Components A and B can cause severe inhalation and skin sensitization. For interior applications: full body protection required. A comprehensive review of SPF safety and handling can be found on the [CPI website](#).

**Fire** — Polyurethane foam may present a fire hazard if exposed to fire or excessive heat (i.e., cutting torches). Polyurethane foam systems should not be left exposed and must be protected by a minimum 15-minute thermal barrier or other code-compliant material as prescribed by applicable building code(s). Proper authorities with jurisdiction over a particular area should always be consulted for additional or specific requirements prior to beginning any project.

## Ventilation and Implications for Re-Entry/Re-Occupancy

During application of Natural Polymers Natural-Therm® Pro, a minimum of 10 ACH is recommended and maintained for **at least three hours post spraying prior to re-entry** of trade workers and **24 hours for re-occupancy**. Cross-ventilation is required with negative pressure in the spray area and exhaust to a secured empty area. If recommended ventilation rates cannot be achieved, a 24-hour re-entry time and re-occupancy time is recommended for trade workers and building occupants. For more detailed information, please visit [American Chemistry Council](#).

## Temperature and Humidity

Recommended substrate temperatures:

	Summer	Winter
Minimum	32°F	20°F
Maximum	120°F	77°F

Moisture in the form of rain, dew, and frost can seriously affect the quality and adhesion of the Natural-Therm® Pro to the substrate or itself. Natural Polymers does not recommend the spraying of this system when the relative humidity (RH) exceeds 85% or when temperatures are less than 5°F above dew point. When heating the interior of a building, the relative humidity can change dramatically and should be constantly monitored to ensure proper application.

## Surface Preparation

Natural-Therm® Pro must be applied to surfaces that are clean and dry and free of dirt, oil, solvent, grease, loose particulates, frost, ice, and other foreign matter that could inhibit adhesion.

SUBSTRATE	CONSIDERATIONS	PRIMING
Wood (OSB, Plywood, Lumber)	Moisture <18%	Not required unless porosity or moisture issues exist <sup>1</sup>
Concrete (CMU, Structural, Pour-in-Place)	28-day min. cure	Not required unless specified or adhesion testing supports <sup>1</sup>
Metal (Steel, Painted, Aluminum, <sup>1</sup> Galvanized <sup>1</sup> )	Clean of oils, dry	May be required based on adhesion testing; Recommended for Al, Galvanized Surfaces <sup>1</sup>
Plastics (PVC, CPVC)	Compatible	Not required

<sup>1</sup> SPFA-143 — Primers for Spray Polyurethane Foam Insulation and Roofing Systems.

## Spraying

Natural-Therm® Pro is designed to provide optimal yield when sprayed in 2-inch- to 4-inch-thick passes. Excessive pass thickness above 4 inches can reduce physical properties and cause local overheating and possible fire. Additional thickness may be applied when the surface temperature of the foam is less than 100°F. Yield and in-place density are dependent upon the temperature of the substrate, ambient air temperature, gun speed of application, gun tip size, and the output of the proportioner. In freezing conditions, job site air temperature must be consistently maintained above 32 degrees to ensure proper curing.


Risk of over processing increases when multiple factors are pushed to the limits of application guidance. For example, spraying at the maximum pass and the high/low end of substrate temperatures at the same time can increase the likelihood of failure.

## Processing Guidance

	SUMMER	WINTER
Ambient Temperature	32°F–120°F	20°F–77°F
<b>MACHINE SETTING TEMPERATURE</b>		
A Component Pre-heaters	99°F–125°F	110°F–130°F
B Component Pre-heaters		
Hoses		
Spray Pressure (Dynamic) <sup>2</sup>	1,200–1,600 psi	
<b>PROCESSING CHARACTERISTICS</b>		
Cream Time	1–2 (Seconds)	0.5–2 (Seconds)
Tack-Free Time	6–7 (Seconds)	4–5 (Seconds)
Initial Cure Time <sup>1</sup>	<1 Hour	<1 Hour

<sup>1</sup> Complete cure will depend on temperature, humidity, and degree of ventilation. Complete cure usually occurs within 24–72 hours.

<sup>2</sup> Higher pressures improve mixing and influence physical property performance.



## Certifications and Sustainable Features



## Disclaimer of Warranties and Limitation of Liability

Natural Polymers warrants only that the products shall be manufactured in accordance with Natural Polymers published specifications. Natural Polymers disclaims all other warranties, whether express or implied, including the implied warranties of merchantability, fitness for a particular purpose, and non-infringement of any intellectual property rights, all of which are expressly excluded. To the fullest extent permitted under applicable law, Natural Polymers shall not be liable for incidental, consequential (including any lost profits) or special damages, punitive damages, or for damage to the building, its contents, or its occupants. Natural Polymers total liability and the exclusive remedy for all proven claims is replacement of the nonconforming product, and in no event shall Natural Polymers be liable for any other damages.

No statement or recommendation made or assistance given by Natural Polymers, or its representatives, either oral or in any literature or other documentation, to the buyer, its customers or any other persons in connection with the purchase, use or installation by buyer, its customers or any other persons, of any product sold by Natural Polymers, shall constitute a waiver by Natural Polymers of any provision hereof or affect Natural Polymers liability.

For more information, visit:  
[www.owenscorning.com/naturalpolymers](http://www.owenscorning.com/naturalpolymers)

**NATURAL POLYMERS, LLC**  
 14438 E. NORTH AVE., CORTLAND, IL 60112

**1-800-GET-PINK**

Pub. No. 10028293. Printed in U.S.A. April 2026. ©  
 2026 Natural Polymers, LLC. All Rights Reserved.