



# FOAMULAR® NGX® CODEBORD®

## AIR BARRIER SYSTEM

Owens Corning® FOAMULAR® NGX® CodeBord® Extruded Polystyrene (XPS) Insulation is a closed-cell, moisture-resistant rigid foam board well suited to meet the needs of a wide variety of building applications.<sup>1</sup> Combine in a system with acrylic sheathing tape (JointSealR®), flashing tape (FlashSealR®), and polyethylene foam sill gasket (ProPINK ComfortSealR™) to form and function as a complete exterior air barrier system.


### Product Features



**SUPERIOR  
MOISTURE  
RESISTANCE**



**DURABLE**



**EASY TO CUT,  
FORM & FIT**



**80% GLOBAL  
WARMING  
REDUCTION<sup>1</sup>**

<sup>1</sup> Impact measured over 100-year time horizon, as compared to legacy FOAMULAR® insulation. EPD can be found in the "Environmental and Sustainability" section on Page 2.

### Basic Uses/Related Uses

- Exterior air barrier system for above grade wall assemblies with maximum stud spacing of 610 mm (24") o.c. and maximum building height of 12 m (39' 4")

### Selection Criteria

- XPS foam board insulation function as: thermal, air, and weather control layers
- Exterior air barrier system
- Moisture resistant (hydrophobic), long term durability
- Reduces thermal bridging
- Warms wall cavity, reduces risk of condensation

### Performance Criteria

<b>COMPLIANCE</b>	CCMC Evaluation Listing No. 12935-R Type 3	CCMC CAN/ULC-701.1-17
-------------------	---	--------------------------

### Additional Performance Information

PROPERTY	VALUE	TEST METHOD
Thermal Resistance <sup>2</sup>	RSI, °C·m <sup>2</sup> /W (R-Value, hr·ft <sup>2</sup> ·°F/Btu) 5.0 (0.88) @ 24 °C (75 °F) mean temperature 5.4 (0.95) @ 4.4 °C (40 °F) mean temperature 5.6 (0.99) @ -3.9 °C (25 °F) mean temperature	ASTM C518 or C177
LTTR: (Canada)	Min. LTTR RSI (m <sup>2</sup> °C/W) RSI: 0.65 @ 19 mm thickness RSI: 0.87 @ 25.4 mm thickness RSI: 1.27 @ 38.1 mm thickness RSI: 1.67 @ 50.8 mm thickness RSI: 2.09 @ 63.5 mm thickness RSI: 2.51 @ 76.2 mm thickness RSI: 2.93 @ 88.9 mm thickness RSI: 3.36 @ 101.6 mm thickness	CAN/ULC-S770-15
Compressive Strength <sup>3</sup>	20 psi (140 kPa)	ASTM D1621
Compressive Modulus (typical)	1000 psi (6895 kPa)	ASTM D1621
Flexural Strength <sup>4</sup> (typical)	70 psi (483 kPa)	ASTM C203
Dimensional Stability, Maximum	% linear change: 1.5	ASTM D2126
Linear Coefficient of Thermal Expansion	6.3 x 10 <sup>-5</sup> mm/mm/°C (3.5 x 10 <sup>-5</sup> in./in./°F)	ASTM E228
Water Absorption	(max % by volume): 0.70 (max % by volume): 0.30	ASTM D2842 ASTM C272 <sup>5</sup>
Water Vapour Permeance (typical)	> 0.52 Perms (30 ng/Pa.s.m <sup>2</sup> ) and < 1.05 Perms (60 ng/Pa.s.m <sup>2</sup> )	ASTM E96
Water Capillarity	None	-
Water Affinity	Hydrophobic	-
Limiting Oxygen Index	min.: 24	ASTM D2863
Non-combustibility	Combustible	CAN/ULC-S114
Surface Burning Characteristics	Flame Spread 90, Smoke Developed > 350	CAN/ULC-S102.2
Max. Service Temperature	74 °C (165 °F)	-
Air Permeability	75 Pa (L/s.m <sup>2</sup> ): Negligible (0.001) <sup>6</sup>	-

<sup>2</sup> The R-value for FOAMULAR® NGX® XPS Insulation is provided from testing at mean temperatures of: -4°C (25°F), 4.4°C (40°F), and 24°C (75°F) and aging techniques of 180-day real time aged (as mandated by ASTM C578) and accelerated aging "Long-Term Thermal Resistance" (LTTR) per CAN/ULC S770-03.

<sup>3</sup> Values at yield or 10% deflection, whichever occurs first.

<sup>4</sup> Value at yield or 5%, whichever occurs first.

<sup>5</sup> Per method described in ASTM C578

<sup>6</sup> Air permeance rate of FOAMULAR® CodeBord® tested by ORTECH. Test results were published in report 970J53-M0071-A April 23, 1998.

Technical Information

- Deliver products in their original packages, and store in enclosed shelter. Packaging is not UV resistant. Shelter unused packages from the elements.
- Exposure to exterior conditions during normal construction cycles is permitted. During that time some fading of color may begin due to UV exposure, and, if exposed for extended periods of time, some degradation or "dusting" of the polystyrene surface may begin. It is best if the product is covered within 60 days to minimize degradation. Once covered, the deterioration stops, and damage is limited to the thin top surface layers of cells. Cells below are generally unharmed.
- Prior to use of adhesives, sealants or other similar products with polystyrene boards, verify their compatibility with adhesive manufacturers.
- This product is combustible and may constitute a fire risk if not used or installed properly. Although it contains a fire-suppressing agent, the product will ignite if exposed to a sufficiently intense flame. Do not expose to open flames or any other ignition source during transport, handling, storage or use. A protective barrier or thermal barrier is required to separate this product from interior living or conditioned spaces as specified in the appropriate building code.
- For installation instructions on the FOAMULAR® CodeBord® Air Barrier System see publication no. 500637 or visit [www.owenscorning.ca](http://www.owenscorning.ca) for videos and further information.

Availability


PRODUCT	THICKNESS	WIDTHS	LENGTHS	EDGES
FOAMULAR® NGX® C-200 XPS <sup>A</sup>	25 mm - 102 mm (1" - 4") in 13 mm (½") increments	610 mm (24")	2438 mm (96")	Square or Ship Lapped
FOAMULAR® NGX® CodeBord® XPS	25 mm - 89 mm (1" - 3.5")	610 mm & 1220 mm (24" & 48")	2438 mm, 2743 mm, 3048 mm (96", 108", 120")	Square or Ship Lapped

FOAMULAR® NGX® C-200 is shipped in units containing four individually shrink-wrapped packages and FOAMULAR® NGX® CodeBord® is shipped in units containing three individually shrink-wrapped packages.

<sup>A</sup>Metric sizes for CMU also available

Certifications and Sustainable Features

- Certified by SCS Global Services to contain a minimum of 20% recycled content pre-consumer #SCS-RC-01132.
- GREENGUARD Certified products are certified to GREENGUARD standards for low chemical emissions into indoor air during product usage. For more information, visit <https://www.ul.com/gg>
- Environmental Product Declaration (EPD) has been certified by SCS Global Services. EPD #SCS-EPD-09753.
- UL CERTIFIED — See Bulk Shipment Certificate U-197 available at [www.owenscorning.com/U197](http://www.owenscorning.com/U197).
- Contributes to credits in green building programs such as LEED® and Green Globes. For further information see documents: LEED® v4 for Building Design and Construction and Owens Corning Impact Study - Leadership in Energy and Environmental Design (LEED® v4)



Environmental and Sustainability

Owens Corning is a worldwide leader in building material systems, insulation, and composite solutions, delivering a broad range of high quality products and services.

Owens Corning is committed to driving sustainability by delivering solutions, transforming markets, and enhancing lives. More information can be found at [www.owenscorning.ca](http://www.owenscorning.ca) or [www.owenscorninglibrary.ca](http://www.owenscorninglibrary.ca).

FOAMULAR® NGX® XPS insulation uses blowing agents with zero ozone depletion potential.

Detailed environmental information on the lifecycle of this product can be found in product's Environmental Product Declaration.

Technical Services Available

For Canadian Technical inquiries, please contact our technical team at [www.owenscorning.ca/contacttech](http://www.owenscorning.ca/contacttech).

Limited Warranty

FOAMULAR® NGX® XPS insulation limited lifetime warranty maintains 90% of its R-value for the lifetime of the building and covers all CAN/ULC-S701 properties. See FOAMULAR® NGX® Extruded Polystyrene Insulation Lifetime Limited Warranty for complete details, limitations, and requirements.

Disclaimer of Liability

Technical information contained herein is furnished without charge or obligation and is given and accepted at recipient's sole risk. Because conditions of use may vary and are beyond our control, Owens Corning makes no representation about and is not responsible or liable for the accuracy or reliability of data associated with particular uses of any product described herein. SCS Global Services provides independent verification of recycled content in building materials and verifies recycled content claims made by manufacturers. For more information, visit [www.SCSglobalservices.com](http://www.SCSglobalservices.com).

LEED® is a registered trademark of the U.S. Green Building Council.

Notes

For additional information, refer to the Safe Use Instruction Sheet (SUIS) found in the SDS Database via <http://sds.owenscorning.com>.

**OWENS CORNING CANADA LP**  
3450 MCNICOLL AVENUE  
SCARBOROUGH, ONTARIO M1V 1Z5  
**1-800-GET-PINK®**  
[www.owenscorning.ca](http://www.owenscorning.ca)