



THERMAFIBER® RAINBARRIER® CI HIGH COMPRESSIVE (80) MINERAL WOOL INSULATION

Features

- High compressive strength to support cladding attachment system with minimal penetration through continuous insulation
- More than 10% lighter in weight than the leading competitor's product
- Vapour permeable
- Tolerant of substrate irregularities
- Non-combustible and non-deteriorating
- Fire-resistant to temperatures above 1,093°C (2,000°F)
- Enhances acoustical performance
- Minimum 70% recycled content¹
- Contributes to credits in several green building programs such as LEED® and Green Globes®

Standards, Codes Compliance

- CCMC Evaluation Listing No. 14060-L
- CAN/ULC-S702.1, Standard for Mineral Fibre Thermal Insulation for Buildings, Type 1
- ASTM C612, Mineral Fiber Block and Board Thermal Insulation, Types IA, IB, II, III, IVA, IVB
- RainBarrier® CI High Compressive 80 can be used as a thermal barrier for foamed plastics, certified to CAN/ULC-S124. See QAI Listing No. B1079 for details

Technical Data

		TESTED TO ASTM C518	
NOMINAL DENSITY		RSI / 25.4 MM @ 24 °C M ² ·K/W	R-VALUE/INCH @ 75 °F HR·FT ² ·°F/BTU
128 kg/m ³ (8.0 pcf)		0.74	4.2

Acoustical Performance

THICKNESS	TESTED TO ASTM C423 SOUND ABSORPTION COEFFICIENTS AT OCTAVE BAND CENTER FREQUENCIES (Hz)						
	125 Hz	250 Hz	500 Hz	1000 Hz	2000 Hz	4000 Hz	NRC
51 mm (2")	0.22	0.90	1.05	1.06	1.02	1.04	1.00

Thermafiber® RainBarrier® ci High Compressive (80) continuous insulation boards are designed to support cladding attachment with minimal penetrations. The use of ThermaCrimp™ technology allows for excellent compressive strength while providing thermal efficiency, non-combustibility, water repellency, and flexibility when working with uneven substrates. RainBarrier® ci High Compressive (80) can be used behind light weight cladding – including combustible and open-joint assemblies.

Performance Criteria

COMPLIANCE	CCMC Evaluation Listing No. 14060-L Type 1	CCMC CAN/ULC-S702.1
------------	-----------------------------------------------	------------------------

Additional Performance Information

PROPERTY	VALUE	TEST METHOD
Compressive Strength	22.7 kPa (475 lbs/ft ²) @ 10% deformation	ASTM C165
Surface Burning Characteristics	Flame Spread 0, Smoke Developed 5	CAN/ULC-S102
	Flame Spread 0, Smoke Developed 0	ASTM E84
Non-Combustibility	Complies	CAN/ULC-S114
	Non-Combustible as defined per NFPA 220	ASTM E136
Smoulder Resistance	Mean Mass Loss ≤ 0.02%	CAN/ULC-S129
Linear Shrinkage	<2% @ 650 °C (1,200 °F)	ASTM C356
Water Vapour Permeance	1,373 ng/Pa·s·m ² (24 Perms)	ASTM E96
Water Vapour Sorption	Sorption less than 0.5% by volume	ASTM C1104
Fungi Resistance	Complies	ASTM C1338
Corrosion of Steel, Aluminum, and Copper	Pass	ASTM C665
Stress Corrosion – Austenitic Steel	Pass	ASTM C795
Odor	Pass	ASTM C1304

Availability

THICKNESS ²	STANDARD DIMENSIONS
38 mm - 152 mm (1.5" - 6")	610 mm x 1219 mm (24" x 48") 1219 mm x 1829 mm (48" x 72")

2 Thicknesses are available in 13 mm (½") increments

Installation

Thermafiber, Inc. recommends mechanical attachment of Thermafiber® RainBarrier® CI HC insulation products. See Owens Corning publication "Thermafiber® RainBarrier® CI High Compressive – Cladding Attachment Guide Canada" (Pub. No. 600224) for more information.

Certifications and Sustainable Features

- Verified by ICC-ES to contain a minimum of 70% recycled content. See ICC-ES Evaluation Report VAR-1025 at icc-es.org.
- Environmental Product Declaration (EPD) has been certified by UL Environment. For more information visit ul.com/epd.
- Rainbarrier® Products have a published Health Product Declaration (HPD).
- Living Building Challenge Compliant and Red List Approved.



Environmental and Sustainability

Owens Corning is a worldwide leader in building material systems, insulation, and composite solutions, delivering a broad range of high-quality products and services.

Owens Corning is committed to driving sustainability by delivering solutions, transforming markets, and enhancing lives. More information can be found at www.owenscorning.ca or www.owenscorninglibrary.ca.

Technical Services Available

For Canadian Technical inquiries, please contact our technical team at www.owenscorning.ca/contacttech.

Disclaimer of Liability

Thermafiber, Inc. shall not be liable for incidental and consequential damages, directly or indirectly sustained, nor for any loss caused by application of these goods not in accordance with current printed instructions or for other than the intended use. Thermafiber, Inc. liability is expressly limited to replacement of defective goods. Any claim shall be deemed waived unless made in writing within thirty (30) days from date it was or reasonably should have been discovered.

UL and the UL logo are trademarks of UL LLC.

Notes

For additional information, refer to the Safe Use Instruction Sheet (SUIS) found in the SDS Database via <http://sds.owenscorning.com>.